National Library
of Canada

Acquisitions and
Bibliographic Services Branch

395 Wellington Street
Ottawa, Ontario
K1A 0N4

Bibliothèque nationale
du Canada

Direction des acquisitions et
des services bibliographiques

395, rue Wellington
Ottawa (Ontario)
K1A 0N4

Veuillez noter : Votre référence

Cette notice : Notre référence

NOTICE

The quality of this microform is heavily dependent upon the quality of the original thesis submitted for microfilming. Every effort has been made to ensure the highest quality of reproduction possible.

If pages are missing, contact the university which granted the degree.

Some pages may have indistinct print especially if the original pages were typed with a poor typewriter ribbon or if the university sent us an inferior photocopy.

Reproduction in full or in part of this microform is governed by the Canadian Copyright Act, R.S.C. 1970, c. C-30, and subsequent amendments.

AVIS

La qualité de cette microforme dépend grandement de la qualité de la thèse soumise au microfilmage. Nous avons tout fait pour assurer une qualité supérieure de reproduction.

S'il manque des pages, veuillez communiquer avec l'université qui a conféré le grade.

La qualité d'impression de certaines pages peut laisser à désirer, surtout si les pages originales ont été dactylographiées à l'aide d'un ruban usé ou si l'université nous a fait parvenir une photocopie de qualité inférieure.

La reproduction, même partielle, de cette microforme est soumise à la Loi canadienne sur le droit d'auteur, SRC 1970, c. C-30, et ses amendements subséquents.

Canada

Cobalt Site Preferences in Iron Rare-earth Based Compounds

by

Lexiang Liao, M.Sc.

Department of Physics, McGill University

Montréal, Canada

August 1992

**A Thesis submitted to the
Faculty of Graduate Studies and Research
in partial fulfillment of the requirements for the degree of
Doctor of Philosophy**

© Lexiang Liao, 1992

National Library
of Canada

Acquisitions and
Bibliographic Services Branch

395 Wellington Street
Ottawa, Ontario
K1A 0N4

Bibliothèque nationale
du Canada

Direction des acquisitions et
des services bibliographiques

395, rue Wellington
Ottawa (Ontario)
K1A 0N4

Author: Université de Montréal

Editor: Bibliothèque nationale

The author has granted an irrevocable non-exclusive licence allowing the National Library of Canada to reproduce, loan, distribute or sell copies of his/her thesis by any means and in any form or format, making this thesis available to interested persons.

L'auteur a accordé une licence irrévocable et non exclusive permettant à la Bibliothèque nationale du Canada de reproduire, prêter, distribuer ou vendre des copies de sa thèse de quelque manière et sous quelque forme que ce soit pour mettre des exemplaires de cette thèse à la disposition des personnes intéressées.

The author retains ownership of the copyright in his/her thesis. Neither the thesis nor substantial extracts from it may be printed or otherwise reproduced without his/her permission.

L'auteur conserve la propriété du droit d'auteur qui protège sa thèse. Ni la thèse ni des extraits substantiels de celle-ci ne doivent être imprimés ou autrement reproduits sans son autorisation.

ISBN 0-315-87616-6

Canada

TO MY FATHER

Abstract

This thesis presents the first systematic study of the cobalt site preferences in iron rare-earth based compounds. The Mössbauer source technique employed in this work offers a direct and unambiguous way to quantitatively determine cobalt site preferences in these compounds at extremely low cobalt contents. Data quality as well as counting efficiency for the source (^{57}Co doped) samples is enhanced by constructing a resonant conversion electron detector utilising 90% ^{57}Fe enriched stainless steel foil. Our results have produced the most convincing evidence that cobalt substitutes preferentially for iron in these compounds. We have demonstrated that the site volume is the dominant factor controlling the preferential cobalt substitutions at transition-metal sites with volume $< 12.2\text{\AA}^3$. The cobalt preference for a site decreases linearly with increasing site volume at a rate of $\sim 0.9\text{\AA}^{-3}$. In general, cobalt shows a preference for sites with volume $< 11.8\text{\AA}^3$. As site volume becomes sufficiently large ($\geq 12.2\text{\AA}^3$), the negative enthalpy of mixing between cobalt and rare-earth plays a significant role in modifying the cobalt site preferences in combination with the site volume effects. This results in cobalt preferring strongly those sites with the highest number of rare-earth nearest-neighbors.

Résumé

Cette thèse présente la première étude systématique des sites préférentiels du cobalt dans les composés de fer et de métaux de terres rares. La technique de source Mössbauer employée dans cet ouvrage est une façon directe et sans ambiguïté de déterminer quantitativement les sites préférentiels du cobalt dans ces composés avec un contenu de cobalt extrêmement faible. La qualité des données ainsi que l'efficacité du comptage pour les échantillons de ^{57}Co sont augmentées par la construction d'un détecteur d'électrons à conversion résonante qui utilise des feuilles d'acier inoxydable enrichi à 90% en ^{57}Fe . Nos résultats représentent la plus convainquante évidence que le cobalt se substitue préférentiellement pour le fer dans ces composés. Nous avons démontré que le volume du site est le facteur qui domine la substitution préférentielle du cobalt sur les sites des métaux de transition avec un volume $< 12.2\text{\AA}^3$. La préférence du cobalt pour un site décroît linéairement avec l'augmentation du volume du site, à un taux de $\sim 0.9\text{\AA}^{-3}$. En général, le cobalt montre une préférence pour les sites avec un volume $< 11.8\text{\AA}^3$. Lorsque le volume du site devient assez grand ($\geq 12.2\text{\AA}^3$), l'enthalpie négative du mélange entre le cobalt et les métaux de terres rares joue un rôle significatif dans la préférence du cobalt pour un site, venant s'ajouter à l'effet de volume. Ceci mène à ce que le cobalt préfère fortement les sites qui ont le plus grand nombre de terres rares comme proches voisins.

Acknowledgements

It is my genuine pleasure to thank my thesis supervisor, Professor Zaven Altounian, for his guidance and support. Throughout the course of my thesis work, I have benefited enormously from his constant advice and encouragement. I am grateful to Professor Dominic H. Ryan for his help with the Mössbauer experiments, and for his critical reading of the thesis. It was him who introduced me to the Mössbauer technique. I also wish to thank Professors John Ström-Olsen and W. Burnett Muir for their support. I am indebted to Frank van Gils and John Egyed for technical assistance and to Diane Kozial, Betty Pederson, and Paula Domingues for their help in dealing with all the administrative work. Thanks are also due to Eric Dufresene who translated the abstract.

I appreciate greatly the friendship with Guo Hong, Yao Jian Hua, Mao Ming, Bian Xiao Ping, Ren Hong, Martin Lacasse, and many other graduate students in Solid State Physics group. The good time I enjoyed with the members of basketball team will be memorable.

Finally, I owe a lot of thanks to my wife, Yan, for her many sincere advices throughout all these years of my studying at McGill.

Contents

Abstract	i
Résumé	ii
Acknowledgements	iii
Table of contents	iv
List of Figures	vi
List of Tables	viii
1 Introduction	1
2 Mössbauer Spectroscopy	21
2.1 Basic Principles	21
2.2 Hyperfine Interactions	26
2.2.1 Isomer Shift	26
2.2.2 Magnetic Hyperfine Interaction	29
2.2.3 Quadrupole Interaction	32
2.2.4 Combined Quadrupole and Magnetic Hyperfine Interaction . .	33
2.3 Analysis of Mössbauer Spectra	35
3 Experimental Methods	38
3.1 Sample Preparation and Characterization	38
3.1.1 Sample Preparation	38
3.1.2 Characterization	40
3.2 Mössbauer Experiments	42
3.3 Conversion Electron Detector	46
3.3.1 Detector Description	49
3.3.2 Detector Performance	52

4	Results and Discussion	58
4.1	Mössbauer Spectra and Site Preferences	56
4.1.1	$\text{Nd}_2\text{Fe}_{14}\text{B}$	56
4.1.2	R_2Fe_{17} (R = Nd, Gd, Dy)	67
4.1.3	$\text{Er}_6\text{Fe}_{23}$	79
4.1.4	DyFe_3	85
4.1.5	ThFe_5	91
4.2	Discussion	97
5	Conclusions	109
	Appendix A	111
	References	116

List of Figures

1.1	Magnetic characteristics of $\text{Nd}_2\text{Fe}_{14-x}\text{Co}_x\text{B}$ alloys as functions of Co contents	3
1.2	Unit cells of $\text{Nd}_2\text{Fe}_{14}\text{B}$, R_2Fe_{17} , and RFe_5	5
1.3	Neutron diffraction pattern for $\text{Nd}_2(\text{Fe}_{0.5}\text{Co}_{0.5})_{17}$	8
1.4	Mössbauer spectra of $\text{Nd}_2(\text{Fe}_{1-x}\text{Co}_x)_{14}\text{B}$ obtained at 295 K	10
1.5	The ^{57}Fe NMR spectra in the ^{10}B substituted $\text{Nd}_{15}\text{Fe}_{77-x}\text{Co}_x\text{B}_8$ at 4.2 K	12
2.1	Schematic drawing of the nuclear resonance	22
2.2	a) Basic arrangement for measuring a Mössbauer spectrum in transmission geometry and b) Nuclear decay scheme of ^{57}Co	24
2.3	Mössbauer spectrum for $\alpha\text{-Fe}$ foil at 295 K	25
2.4	Energy level diagram and resultant spectra for ^{57}Fe	27
2.5	Mössbauer spectrum for a stainless steel foil at 295 K	28
2.6	Mössbauer spectrum of $\text{Nd}_2\text{Fe}_{14}\text{B}$ at 295 K	32
2.7	Orientation of the magnetic hyperfine field relative to V_{xx}	34
2.8	Mössbauer spectrum of TbFe_2 at 77 K	37
3.1	(a) X-ray diffraction pattern for $\text{Dy}_2\text{Fe}_{17}$ and (b) TGA curve for as-made sample of ThFe_5	41
3.2	Schematic diagram of a Mössbauer spectrometer	43
3.3	A schematic diagram of internal conversion process for the 14.4 keV transition of ^{57}Fe	47
3.4	Sectional views of the detector	50
3.5	Pulse height spectrum obtained using a 74 MBq ^{57}Co source	52
3.6	Mössbauer spectra of 310 stainless steel	53
4.1	X-ray diffraction pattern and TGA curve of the reference sample for $\text{Nd}_2\text{Fe}_{14}\text{B}$	58
4.2	Mössbauer spectrum of reference sample for $\text{Nd}_2\text{Fe}_{14}\text{B}$	59
4.3	Mössbauer spectrum of source sample for $\text{Nd}_2\text{Fe}_{14}\text{B}$	62
4.4	Mössbauer spectrum of reference and source samples for $\text{Nd}_2\text{Fe}_{14}\text{B}$	63

4.5	The percentage deviation of fitted Co site occupations from random occupation for the $\text{Nd}_2\text{Fe}_{14}\text{B}$ source	64
4.6	X-ray diffraction patterns for reference samples of R_2Fe_{17}	68
4.7	TGA curves for reference of R_2Fe_{17}	69
4.8	Reference Mössbauer spectra of R_2Fe_{17}	70
4.9	Mössbauer spectrum of the reference and source samples for $\text{Nd}_2\text{Fe}_{17}$ at 77K	74
4.10	Mössbauer spectrum of the reference and source samples for $\text{Gd}_2\text{Fe}_{17}$ at 295K	75
4.11	Mössbauer spectrum of the reference and source samples for $\text{Dy}_2\text{Fe}_{17}$ at 77K	76
4.12	The deviation (%) of the fitted Co site intensities from a random distribution for the Co doped samples of R_2Fe_{17}	77
4.13	X-ray pattern and TGA curve for $\text{Er}_6\text{Fe}_{23}$	80
4.14	Mössbauer spectrum of reference sample for $\text{Er}_6\text{Fe}_{23}$	81
4.15	Mössbauer spectrum of the reference and source samples for $\text{Er}_6\text{Fe}_{23}$	82
4.16	The deviation (%) of fitted Co site occupation from a random distribution for the Co doped $\text{Er}_6\text{Fe}_{23}$	84
4.17	X-ray pattern and TGA curve for DyFe_3	86
4.18	Mössbauer spectrum of reference sample for DyFe_3	87
4.19	Mössbauer spectrum of the reference and source samples for DyFe_3 at 295K	88
4.20	Deviation (%) of fitted site occupations from a random distribution for the Co doped sample	90
4.21	TGA curves for both the as-made and annealed reference samples of ThFe_5	92
4.22	Mössbauer spectrum of reference sample for ThFe_5	93
4.23	Mössbauer spectra of reference source samples for ThFe_5	95
4.24	Deviation (%) of fitted site occupations from a random distribution for the Co doped sample	96
4.25	Plots of site preference vs hyperfine field (B_{hf}) for Fe-R compounds	99
4.26	Wigner-Seitz (i.e. Voronoi) polyhedra for some transition-metal sites in $\text{Nd}_2\text{Fe}_{14}\text{B}$ and $\text{Nd}_2\text{Fe}_{17}$	102
4.27	Plots of site preference vs fraction of Fe neighbors in the total number of neighbors	104
4.28	Site preference (ratio of observed to random occupation) vs average Fe-Fe interatomic distance of the nearest neighbors	105
4.29	Site preference (ratio of observed to random occupation) vs site volume	106

List of Tables

1.1	Summary of observed cobalt site preferences in $\text{Nd}_2\text{Fe}_{14}\text{B}$ and R_2Fe_{17} using neutron diffraction, conventional Mössbauer spectroscopy, and NMR	14
2.1	Angular dependence of the allowed transitions in a pure magnetic interaction	30
3.1	Radiation emitted after resonant absorption of the 14.4 keV by ^{57}Fe .	48
3.2	Summary of conversion electron detector (CED) performance compared with standard transmission measurement (TRANS) on a $8\mu\text{m}$ 310 stainless steel foil	54
4.1	Crystallographic data for R-Fe based compounds	57
4.2	Summary of fitted parameters for the spectrum of $\text{Nd}_2\text{Fe}_{14}\text{B}$	61
4.3	Summary of fitted parameters for the spectra of R_2Fe_{17} (R = Nd, Gd, Dy)	73
4.4	Summary of fitted parameters for the spectrum of $\text{Er}_6\text{Fe}_{23}$	83
4.5	Summary of fitted parameters for the spectrum of DyFe_3	89
4.6	Summary of fitted parameters for the spectrum of ThFe_3	94
4.7	Summary of observed Co occupations and the site preferences as derived from the ratio of observed to random occupation in various Fe-R compounds	98
4.8	Summary of local atomic environment (site volume, type and number of the nearest-neighbors) for iron sites in Fe-R compounds as determined from Wigner-Seitz analysis	101

Chapter 1

Introduction

The recent discovery of the ternary rare-earth-iron-boron compound, $R_2Fe_{14}B$ (R = Rare-earth atom) [1,2], has renewed worldwide research on iron-based rare-earth hard magnetic materials. Considerable technological interest has centered on the prototypical compound $Nd_2Fe_{14}B$ because of its excellent intrinsic magnetic properties and economic advantages over the earlier best magnet materials based on $SmCo_5$. The largest energy product, $(BH)_{max}^1 \sim 45 \text{ MGOe}$ ($\sim 358 \text{ kJ/m}^3$), has been attained in $Nd_2Fe_{14}B$ based magnets [3]. Unfortunately, not all of the magnetic properties of Nd-Fe-B based magnets are superior to those of Sm-Co based magnets. For instance, the coercive forces attainable in Nd-Fe-B materials are much smaller than that of Sm-Co materials, and the high temperature performance of permanent magnets based on $Nd_2Fe_{14}B$ is far from satisfactory because the Curie temperature ($T_c = 585\text{K}$) of $Nd_2Fe_{14}B$ is relatively low ($T_c \sim 1000\text{K}$ for $SmCo_5$).

Many efforts have been made to improve the performance of $Nd_2Fe_{14}B$ based hard magnetic materials. An approach commonly taken is to replace some of the neodymium, iron, or boron of the $Nd_2Fe_{14}B$ compound without altering the crystal

¹The maximum energy product $(BH)_{max}$, which is the maximum product of magnetic induction B and applied field H in the second quadrant of $B(H)$ hysteresis curve, is a figure of merit for a permanent magnet.

structure. The primary objective of these substitutional investigations is the identification of substituents that serve the purpose of enhancing the magnetic properties such as Curie temperature and anisotropy field H_a ². The work on rare-earth substituted $(Nd_{1-x}R_x)Fe_{14}B$ alloys have shown that R replacements for Nd, generally, have a small effect on the Curie temperature (for example, $T_c \sim 660K$ for $Gd_2Fe_{14}B$ is the highest among the $R_2Fe_{14}B$ compounds, only 80 K greater than that of $Nd_2Fe_{14}B$), and while Tb or Dy substitutions markedly enhance the uniaxial anisotropy, it is always at the expense of the saturation magnetization[4]. Boron can only be replaced by carbon. Studies on partially substituted, single phase samples of $Nd_2Fe_{14}B_{1-x}C_x$ with $x \leq 0.75$ indicate that the Curie temperature and saturation magnetization decrease with increasing carbon concentrations, T_c declining by ~ 30 K at $x = 0.5$ [2,5]. Studies on $R_2Fe_{14}B$ with non-magnetic R such as Y and La have demonstrated that the magnetism of the $R_2Fe_{14}B$ compounds originates mainly from the Fe sublattice [6,7]. One expects, therefore, that Fe replacements will have significant effects on the magnetic properties of $Nd_2Fe_{14}B$ based magnet materials. Unlike neodymium and boron for which substituents are limited because of their particular atomic size and chemistry, Fe can be replaced, at least partially, by a large variety of elements which range from the metalloid elements, such as Si, to a large number of transition metals. Among the big pool of elements, however, only cobalt has been found capable of replacing iron over the whole concentration range, while maintaining the integrity of the crystal structure. Figure 1.1a shows the variation of the Curie temperature with Co concentration for $Nd_2Fe_{14-x}Co_xB$; the increase in T_c is most rapid at the lowest Co concentrations, and $T_c(Nd_2Co_{14}B)$

²The anisotropy field H_a measures the external field required to rotate the magnetization from the easy to a hard direction. For example, for $Nd_2Fe_{14}B$ based materials, the value of $\mu_0 H_a$ is $\sim 7.3T$.

Figure 1.1: Magnetic characteristics of $\text{Nd}_2\text{Fe}_{14-x}\text{Co}_x\text{B}$ pseudoternary compounds as functions of cobalt concentration x : (a) Curie temperature T_c and (b) saturation magnetization M_s at 295 K [8]; (c) room temperature anisotropy field [9].

$\sim 1000\text{K}$ is nearly twice the 585K value for $\text{Nd}_2\text{Fe}_{14}\text{B}$. Furthermore, the room temperature saturation magnetization of $\text{Nd}_2\text{Fe}_{14-x}\text{Co}_x\text{B}$ features a modest maximum in the vicinity of $x = 2$, as shown in Fig. 1.1b. Co replacements, therefore, offer the prospect of improving the energy product and high temperature performance of practical magnets based on Nd-Fe-B. There is, however, a negative aspect to Co replacement of Fe; these improvements are offset by a decrease in anisotropy field as shown in Fig. 1.1c [8,9]. Therefore, the best approach to improving the performance of $\text{Nd}_2\text{Fe}_{14}\text{B}$ based magnets is to substitute small amounts of cobalt for iron while offsetting the decline in H_a by other substitutions. For instance, the room temperature H_A of the triply substituted $\text{Nd}_2\text{Fe}_{11.5-y-z}\text{Co}_{2.5}\text{Ga}_y\text{Nb}_z\text{B}$ alloys is observed to increase slightly with y , developing a maximum in the $y \sim 0.15$, $0.1 \leq z \leq 0.2$ region [10].

In order to understand or predict the effects of cobalt substitutions on the magnetic properties of $\text{Nd}_2(\text{Fe}_{1-x}\text{Co}_x)_{14}\text{B}$ and other iron-based rare-earth magnetic materials, it is necessary to know how the cobalt atoms are distributed among the various crystallographically inequivalent iron sites. Figure 1.2 displays the unit cells of the tetragonal $\text{Nd}_2\text{Fe}_{14}\text{B}$, the rhombohedral R_2Fe_{17} , and RFe_5 . As can be seen from Fig. 1.2, the crystal structure of $\text{Nd}_2\text{Fe}_{14}\text{B}$ comprises six crystallographically distinct iron sites, two different rare-earth positions, and one boron site. Differences in chemistry and size will generally prevent the cobalt from occupying the rare-earth and boron sites in the structure. However, it is not obvious that cobalt should substitute randomly among the six crystallographically inequivalent iron sites.

Site preferences³ were observed in some Co substituted binary R-Fe compounds long before the discovery of the $\text{R}_2\text{Fe}_{14}\text{B}$ ternary compounds. The earliest work

³By site preference we refer to the preferential occupation of the replacement atoms among the crystallographically inequivalent atomic sites in a substituted intermetallic compound.

Figure 1.2: a). Tetragonal unit cell of $\text{R}_2\text{Fe}_{14}\text{B}$ ($\text{Nd}_2\text{Fe}_{14}\text{B}$ -type; $p4_2/mnm$) structure (after Herbst and Yelon, 1985 [11]); b). Hexagonal unit cell of the rhombohedral R_2Fe_{17} ($\text{Th}_2\text{Zn}_{17}$ -type; $R\bar{3}m$) structure (after Streever, 1979 [12]); and c). Unit cell of the hexagonal RFe_5 (CaCu_5 -type; $P6/mmm$) structure (adapted from [13]).

reported by Diepen *et al.* (1972 [14]) and Laforest *et al.* (1973 [15]) was done on $\text{Th}(\text{Fe}_{1-x}\text{Co}_x)_5$ alloys, whose crystal structure comprises two crystallographically distinct transition metal sites in the ratio 3:2 (Wyckoff notation 3g and 2c)⁴ (see Fig. 1.2). The Co substitutions in these alloys, as determined by means of neutron diffraction and standard Mössbauer technique⁵, do not occur statistically on the two available sites. The results obtained by these two techniques, however, were contradictory. Neutron diffraction studies [15,16] found an excess Co occupations of the 2c site whereas the results of the standard Mössbauer technique suggested a Co avoidance of this site. Since then, studies on site preferences have been extended to other Co substituted binary R-Fe compounds such as R_2Fe_{17} and RFe_3 , and more recently to the ternary compound $\text{R}_2\text{Fe}_{14}\text{B}$.

The techniques involved in previous studies on Co site preferences in Fe-based rare-earth compounds are mainly neutron diffraction and standard Mössbauer spectroscopy. Recently, nuclear magnetic resonance (NMR) has also been used in studies of preferential Co substitutions in $\text{R}_2\text{Fe}_{14}\text{B}$ [17]. Neutron diffraction studies exploit the differences between neutron-nuclear coherent scattering length b ($b_{\text{Fe}} = 0.95 \times 10^{-14}$ m, $b_{\text{Co}} = 0.28 \times 10^{-14}$ m) to determine the site preferences in Co substituted iron-based compounds. The diffraction patterns spanned in an angular range (2θ), which usually includes a large number of Bragg peaks, are analysed by the standard Rietveld method. For diffraction patterns of materials in magnetically ordered state, there are additional contributions to the patterns from magnetic scattering. In this instance, both magnetic and nuclear parameters are refined for each pattern.

⁴The crystallographic inequivalent M sites are denoted by Wyckoff notation throughout this thesis. The number before the notation indicates the crystallographic multiplicities of each site. The site symmetries are alphabetically ordered with 'a' having the highest symmetry.

⁵The standard Mössbauer technique stands for the widely used transmission Mössbauer method. This name will be used throughout the thesis so as to distinguish it from the Mössbauer source technique.

Besides the usual refinable parameters needed to fit the data, additional parameters for the Co nuclear positions and site occupation numbers are included in the refinements for the Co substituted alloys. In the refinement of data, no constraint is used for total Co and Fe content, but a constraint is imposed such that the sum of the Fe and Co atoms would produce full occupancy at each distinct crystallographic transition metal sites. Because of the difference between b_{Co} and b_{Fe} , the intensities in the diffraction pattern may be significantly changed as a result of Co substitutions for Fe. Therefore the Co site occupations can be deduced from the changes in average scattering length of the calculated diffraction patterns. As an example, the diffraction patterns for $Nd_2(Fe_{0.5}Co_{0.5})_{17}$ taken from reference [18] are shown in Fig. 1.3, where a comparison is made of the diffraction patterns calculated with no restriction on the transition metal site occupancies and that obtained assuming statistical occupation of transition metal sites. As can be seen, the pattern calculated assuming statistical occupation of the transition metal sites does not reproduce the data as well as the pattern fitted with no restriction on transition metal site occupations. The evidence of cobalt preferential substitutions in this alloy is quite clear. However, for low Co concentration alloys, changes in neutron diffraction spectra are not so pronounced. In order to observe a clear site preference, relatively high cobalt concentrations have to be used.

Both Mössbauer and NMR⁶ studies use the ^{57}Fe nucleus as local probes of the magnetic properties of the iron sites to obtain information on the site preferences in Co substituted compounds. In the standard ^{57}Fe Mössbauer studies, the determination of Co site occupations is similar to that used in neutron diffraction, i.e. Co site preferences are deduced from the changes in the iron signal. In general, the

⁶There is also ^{59}Co NMR which can be used in studies of Co substituted iron-based rare earth alloys.

Figure 1.3: (a) in both panels are the observed room temperature neutron diffraction pattern for $\text{Nd}_2(\text{Fe}_{0.5}\text{Co}_{0.5})_{17}$; (b) in the left panel is the pattern calculated with no restriction on transition metal site occupancies and (b) in the right panel is the pattern fitted assuming statistical occupation of TM sites; (c) in both panels are residuals of observed and calculated spectra (after [11]).

observed spectrum may be decomposed into individual subspectra assigned to the crystallographic distinct iron sites, each with its own set of hyperfine parameters. For the cobalt-free alloys, the relative intensities of the subspectra are constrained to the relative iron population ratio corresponding to the crystallographic multiplicities of the transition metal sites. For the Co substituted alloys, however, the relative intensities of the subspectra depend on Co distributions among the sites and thus are not constrained in the fitting of spectrum. The deviation of Co occupations from a random distribution is determined from the fitted spectra. As an example, the Mössbauer spectra of $\text{Nd}_2(\text{Fe}_{1-x}\text{Co}_x)_{14}\text{B}$ alloys obtained by Tharp *et al.* [19] are shown in Fig 1.4. The adjustable parameters in the fitting of the spectra, besides the common parameters such as baseline and linewidth, include the isomer shift, quadrupole splitting, and hyperfine field for each sextet of the six subspectra. The intensities of the subspectra for the $x = 0$ alloy are constrained to the ratio 16:16:8:8:4:4 corresponding to the iron populations of the crystallographic distinct sites k_1 , k_2 , j_1 , j_2 , c , and e (see Fig 1.2a). For cobalt substituted alloys, there is one additional parameter of Fe occupation for each subspectrum as the relative intensities of the subspectra are no longer constrained. The results obtained in this study showed that the relative iron occupations in the j_2 site of $\text{Nd}_2(\text{Fe}_{1-x}\text{Co}_x)_{14}\text{B}$ increase with increasing the Co concentrations [19] while the excess cobalt was found to be near uniformly distributed among the other five sites. The increase of iron population in j_2 is an evidence of iron preferential occupation of this site. Similar to neutron diffraction, this technique requires relatively high Co content in order to see significant changes in spectrum. With increasing Co concentrations, however, the hyperfine fields of the spectra are diminished and the linewidth is broadened because of the distribution of the substituting atom on the near-neighbor sites, which is quite

Figure 1.4: Mössbauer spectra of $\text{Nd}_2(\text{Fe}_{1-x}\text{Co}_x)_{14}\text{B}$ obtained at 295 K (after ref.[19]).

evident from the spectra shown in 1.4. As a result of these effects, the resolution of the spectrum is greatly reduced. Considering that a large number of adjustable parameters are required to fit such poor-resolved spectra, there is undoubtedly a great uncertainty in the final results of the fitting. These problems clearly undermine this technique as a tool to study Co site preference.

^{57}Fe NMR spectroscopy, unlike both neutron diffraction and Mössbauer spectroscopy, is not capable of providing the site occupancies since the intensities of the iron resonant peaks in the NMR spectrum are not simply related to the Fe populations in the sites. An NMR spectrum is a distribution of hyperfine field on the crystallographic distinct iron sites as a function of frequency. The ^{57}Fe NMR resonant frequency is slightly different at each inequivalent iron sites because of differences in local atomic environments. To explain how site preference is determined using NMR, we refer to the NMR experiments performed by Zhang *et al.* on the Co substituted alloys [17]. Figure 1.5 shows the ^{57}Fe NMR spectra for various compositions of ^{10}B substituted⁷ $\text{Nd}_{15}\text{Fe}_{77-x}\text{Co}_x\text{B}_8$ alloys. The seven peaks in the spectrum of $\text{Nd}_{15}\text{Fe}_{77}\text{B}_8$ are attributed to the six iron sites: 4e (41.5 MHz), 4c (44.0 MHz), 16k₁ (44.7 MHz), 8j₁ (46.0 MHz), 16k₂ (48.5 MHz), and 8j₂ (the doublet centered around 52.5 MHz). The effect of Co substitutions on the spectra is seen as a peak shift towards lower frequencies which is an indication of the reduction in the hyperfine fields at the Fe nucleus. The evidence for Co selectivity is obtained from the analysis of these ^{57}Fe line shifts and relative intensity changes in the ^{57}Fe NMR spectrum as well as the effect of Co addition on the local field at B nuclei. From such analysis, Zhang *et al.* find that Co does not preferentially substitute Fe at 4e and 16k₁ sites, but shows a preference for the 16k₂ site. In comparison with neutron

⁷The isotope ^{10}B is used to remove the ^{11}B resonant line, which is in the same frequency range (30–60 MHz) as the ^{57}Fe resonant signal.

Figure 1.5: The ^{57}Fe spectra in the ^{10}B substituted $\text{Nd}_{15}\text{Fe}_{77-x}\text{Co}_x\text{B}$ at 4.2 K (after [17]).

diffraction and standard Mössbauer spectroscopy, NMR is much more indirect and less suitable for studies on site preference.

Co site preferences in $R_2Fe_{14}B$ have been explored by neutron diffraction, standard Mössbauer spectroscopy, and nuclear magnetic resonance (NMR). The results of these studies are summarized in the Table 1.1. Although there is almost unanimous agreement among the studies conducted that Co strongly avoids the $8j_2$ site, the results for the other five sites are conflicting. Neutron diffraction on $Nd_2(Fe_{1-x}Co_x)_{14}B$ [20] reveals a weak Co preference for the $4e$ site while populating the sites $16k_1$, $16k_2$, $8j_1$, and $4c$ randomly. By contrast, NMR measurements find that Co do not occupy either the $4e$ or the $16k_1$ sites, but enters preferentially into the $16k_2$ site [17,32]. Finally, conventional Mössbauer investigations have produced the results that (i) Co prefers the k_2 site and an essentially random distribution among the rest of the sites [19,21–24]; (ii) Co favors the $16k_1$ and $16k_2$ while avoiding the $8j_1$ and $8j_2$ sites [25]; and (iii) no preferential occupancy occurs [26,27]. Obviously, these results add nothing but confusion to the question of the effects of Co substitutions on the magnetic properties of $Nd_2Fe_{14}B$. It should be pointed out that such conflicting results regarding Co substitutions are also found in previous investigations into the Co-substituted binary R-Fe compounds, especially R_2Fe_{17} [18,28–31] as can be seen in Table 1.1. The confusion is at least partially due to the techniques commonly used in determination of site preferences because all of these techniques suffer from one serious defect—the identification of the cobalt sites is indirect as they can only be deduced from the reduction of iron signal. In order to obtain more reliable data on cobalt site preferences, it is essential to use a method which offers direct determination of cobalt locations.

The ideal technique for determination of Co site preferences in iron-based inter-

Table 1.1: Summary of the observed cobalt site preferences in $\text{Nd}_2\text{Fe}_{14}\text{B}$ and R_2Fe_{17} studied by neutron diffraction, conventional Mössbauer spectroscopy, and NMR. A solid circle (•) represents a cobalt preference for the site, a open circle (o) represents Co avoiding the site and a dash line (-) indicates an essentially random occupancy of Co on the site.

<i>Technique</i>	$\text{Nd}_2\text{Fe}_{14}\text{B}$						<i>References</i>
	<i>4e</i>	<i>4c</i>	<i>8j₁</i>	<i>8j₂</i>	<i>16k₁</i>	<i>16k₂</i>	
Neutron diffraction	•	-	-	o	-	-	[20]
Standard	-	-	-	o	-	•	[19,21-24]
Mössbauer spectroscopy	-	-	o	o	•	•	[25]
	-	-	-	-	-	-	[26,27]
NMR	o	-	-	-	o	•	[17]

<i>Technique</i>	R_2Fe_{17}				<i>References</i>
	<i>6c(4f)*</i>	<i>9d(6g)</i>	<i>18f(12j)</i>	<i>18h(12k)</i>	
Neutron diffraction	o	-	•	-	[28] on Y_2Fe_{17}
	o	•	o	•	[18] on $\text{Nd}_2\text{Fe}_{17}$
	(o)	(-)	(-)	(-)	[29] on $\text{Er}_2\text{Fe}_{17}$
Standard	o	-	-	-	[30] on $\text{Tm}_2\text{Fe}_{17}$
Mössbauer spectroscopy	o	-	-	-	[31] on Y_2Fe_{17}

* The site notations are given for the rhombohedral structure with corresponding notations for the hexagonal structure in parentheses.

metallic compounds must satisfy two criteria: (i) *structural sensitivity*—to distinguish crystallographic sites within the structure; (ii) *chemical specificity*—to determine whether the site is occupied by Fe or Co atoms, and what are the fractional occupations. Neutron diffraction provides excellent structural sensitivity, and it can yield a variety of structural and magnetic information with extensive computer analysis, however, it fails criterion (ii) since it does not identify the atoms but measures the average scattering lengths. NMR and standard Mössbauer spectroscopy give extreme selectivity, being sensitive to a single isotope of the particular element being measured, but at the expense of structural information. In general, data analysis requires additional information from structural and magnetic measurements in order to identify observed contributions associated with particular sites in the structure.

The experimental procedures in all cases are the same: (i) a reference (cobalt free) sample is measured to establish a baseline (a standard diffraction pattern or Mössbauer spectrum) and to fix as many structural parameters as possible; (ii) a series of Co-substituted alloys ($\text{Fe}_{1-x}\text{Co}_x$) with $0.1 \leq x \leq 1.0$ are measured, and site preferences are determined by comparison with the reference and by following trends within the series. The cobalt locations are deduced from the reduction in iron signal. As a result, in order to obtain a significant signal, relatively high concentrations of cobalt have to be employed. The lowest concentration, $x \sim 0.1$, is dictated by the limited change in the average scattering length at each site in the diffraction measurements, and the reduction in the intensity of subspectra in the standard Mössbauer method since it detects the iron atoms only. NMR results are further complicated by the absence of any simple relationship between signal strength and site occupancy, Co site preferences being obtained indirectly through changes induced at neighboring sites. At higher Co concentrations, the reliability

of data analysis is seriously affected by the fact that the Co-substituted alloys are significantly different from the reference material. For example, the chemical disorder due to partial substitution can lead to severe broadening of the signal, and the rising significance of cobalt-cobalt interactions can alter the magnetic structure of the alloys.

The Mössbauer source technique used in this work allows direct measurement of cobalt locations, and uses a single Co-doped alloy with $x \sim 10^{-6}$ or less which is, therefore, virtually indistinguishable from the reference material [33]. In a standard Mössbauer experiment a source is prepared by incorporating the parent radio-isotope (^{57}Co in the case of ^{57}Fe) into a matrix (typically Rh or Pd) that yields a single, sharp transition. The γ -rays emitted from the source are then shone through a sample/absorber⁸ and a spectrum is obtained by plotting the transmitted intensity versus the Doppler velocity applied to the source. Each crystallographically distinct site provides a different iron environment and so yields an independent subspectrum. The relative intensities of these subspectra correspond to the distribution of sites in the material.

For a Mössbauer source experiment, the radioactive material (^{57}Co) is incorporated directly into the sample⁹, and the ^{57}Co isotope decays by electron capture with a half life of 270 days to an excited state of ^{57}Fe . The latter subsequently passes to its ground state thereby emitting the 14.4 keV γ -ray that can be used in a standard transmission Mössbauer experiment. The complex emission pattern is analysed using a single-line absorber such as 310 stainless steel foil. The signal comes from ^{57}Fe nuclei in a virtually pure alloy and the observed subspectra are identical to those

⁸The samples used in ^{57}Fe Mössbauer experiments are normally prepared with natural iron materials which contains 2.17% ^{57}Fe in their ground state.

⁹The samples are prepared with the isotope ^{58}Fe rather than natural iron to prevent loss of the signal from resonant self-absorption by the ^{57}Fe present in natural iron

of a standard sample. However, the Fe atoms that emit the radiation are in sites occupied before the electron capture event and thus chosen by cobalt atoms. In other words, only the sites occupied by cobalt atoms contribute to the Mössbauer spectrum. A Co-free sample, serving as a reference, is measured to obtain the best hyperfine parameters for the observed spectrum; and a Co-substituted sample with ^{57}Co doping levels at $\sim 1\text{ppm}$ is measured and the Mössbauer spectrum of the source sample is fitted using the best-fit parameters obtained from the reference spectrum. Only the intensities of the individual subspectra for the source sample are allowed to be adjustable parameters in addition to the off-resonance baseline and linewidth. Because of the extremely low Co doping levels, the reference and source samples are essentially identical in their magnetic and crystal structures. Should cobalt show no preferential substitutions at various iron sites, the observed source spectrum would be exactly the same as that of the reference sample as one would naturally expect. Otherwise, differences between the reference and source spectra will result which may be visually observable. As will be presented in Chapter four of this thesis, the Co site preferences in most of the iron-based compounds studied in this work are indeed seen by a simple visual inspection of the source and reference spectra. The actual Co distributions among the sites are directly determined by simply fitting the spectrum using the parameters obtained from the reference spectrum. It should be emphasized that requiring both the reference and source spectra to be fitted by the same hyperfine parameters with changes only in the intensities of the source spectrum imposes a very severe constraint on the fit and provides a consistency check on the parameters used for the reference spectrum.

In spite of the limitations mentioned above, neutron diffraction studies if properly performed can give valuable information about Co site preferences albeit for higher

Co concentrations. Qualitative information on site preferences, as reported by recent neutron diffraction studies, are reliable. In addition, site preference studies can be performed on a very large number of substitutions and are not limited to Co-Fe substitutions as is the case for the Mössbauer source experiment. The precision of the neutron diffraction results at low Co concentrations is rather poor and quantitative values for site preferences may not be accurate enough to allow the determination of the controlling mechanisms for preferential Co substitutions in R-Fe alloy systems. The Mössbauer source technique with very low Co concentrations can be considered, therefore, complementary to neutron diffraction. The cases where Mössbauer source experiments agree with the extrapolation of neutron diffraction data can be taken as evidence that preferential Co substitutions are not significantly influenced by Co-Co interactions which are negligible in the extreme dilute limit for the Mössbauer source experiment. It should also be mentioned that the very low solubility of Co in certain compounds, such as R_6Fe_{23} , prevents site preference studies being carried out in these compounds using neutron diffraction, NMR or conventional Mössbauer spectroscopy. For the Mössbauer source technique, this represents no additional difficulty as the Co concentrations are of the order of a few *ppm*.

This thesis presents the first systematic study of cobalt site preferences in iron based rare-earth intermetallic compounds. The main objective of this work is to obtain reliable and systematic information on site preferences in an attempt to understand the origin of this subtle phenomenon. We will present data on $Nd_2Fe_{14}B$ and some representative R-Fe equilibrium binary phases which contain at least two crystallographically distinct iron sites. The particular binary compounds selected for study are Nd_2Fe_{17} , Gd_2Fe_{17} , Dy_2Fe_{17} , Er_6Fe_{23} , $DyFe_3$, and $ThFe_6$ ¹⁰. Although

¹⁰Strictly speaking, Thorium is an Actinide. However, because of its similarity in chemistry and size to the Lanthanides we shall refer to it as a rare-earth

the type of rare-earth atom affects the magnetic properties of these compounds, there is no reason to believe that site preference on the transition metal lattice will be markedly influenced by the choice of rare earth atom. As a matter of fact, we will show in subsection 4.1.2 that our results on the two hexagonal $\text{Dy}_2\text{Fe}_{17}$ and $\text{Gd}_2\text{Fe}_{17}$ are identical and thus confirm this argument. Therefore, it is unnecessary to carry out a complete study of all existing R-Fe binary compounds. $\text{Nd}_2\text{Fe}_{14}\text{B}$ is chosen because of its technological importance as a permanent magnet material and to evaluate the considerable amounts of conflicting data on Co site preference in this compound. The binary compounds selected represent a variety of crystal structures and provide a large number of crystallographic sites with various symmetries and local environments. The representative selection criteria for the R-Fe compounds were: (i) the compounds have relatively high Curie temperatures so that it is possible to obtain a well-resolved Mössbauer spectrum and (ii) single phase alloys can be easily obtained as it is essential to eliminate impurity phases which affect the determination of site occupancy. In view of the possible effect of structural differences on Co site preference, three R_2Fe_{17} compounds have been included in this study as these compounds exist in two closely related structural modifications; hexagonal ($\text{P6}_3/\text{mmc}$) and rhombohedral ($\text{R}\bar{3}\text{m}$). Alloys of $\text{Nd}_2\text{Fe}_{17}$ and $\text{Dy}_2\text{Fe}_{17}$ have the rhombohedral and hexagonal structures, respectively, while $\text{Gd}_2\text{Fe}_{17}$ could have both structure types. ThFe_5 is selected as it is the only known RFe_5 compound, and its structure with only two crystallographically inequivalent iron sites is the simplest crystal structure in which site preferences can be observed.

In the next chapter, the basic principles of the Mössbauer spectroscopy are described. Chapter three gives details of sample preparation and characterization techniques. Also included in this chapter is a detailed description of a resonant

conversion electron detector which was constructed for the Mössbauer source experiments. This detector enhances the data counting efficiency and allows Mössbauer source measurements to be made with the source at liquid nitrogen temperature (77K). The results for Co site preference are presented and discussed in Chapter four. They are analyzed in terms of near-neighbor environment and cell volume for each atomic site based on a Wigner-Seitz analysis of the crystal structure. Finally, the conclusions derived from this analysis are summarized in Chapter 5.

Chapter 2

Mössbauer Spectroscopy

2.1 Basic Principles

Mössbauer spectroscopy¹ uses the recoil-free resonant emission or absorption of γ -rays in a solid matrix, i.e. emission and absorption of γ -rays without the loss of energy to the lattice. Because of the recoil-free nature of the emission and absorption process, the energy distribution of the γ -rays is dictated by the Heisenberg uncertainty principle and has a Lorentzian lineshape centered at E_γ with the natural linewidth of the transitions [37]. The theoretical resolution of the technique is thus determined by the natural linewidth of the nuclear transition or the lifetime of the excited state of the nuclear transitions [38]. For ^{57}Fe Mössbauer spectroscopy, the natural linewidth of the 14.4 keV transition is $4.6 \times 10^{-9} \text{ eV}$ ($1 \text{ eV} = 1.60219 \times 10^{-19} \text{ J}$). In the remainder of this section, we will describe briefly how the recoil-free γ -ray emission process is achieved.

Figure 2.1 shows a schematic drawing of the nuclear resonant transitions between excited and ground states in two nuclei. Let us consider an isolated atom of mass M with an excited state level at an energy E_0 . When a γ -ray of energy E_γ is emitted, the atom recoils with a recoil kinetic energy E_R . By the conservation of energy, the

¹More detailed description of Mössbauer spectroscopy can be found in references [34–37].

actual energy of the emitted γ -ray is given by

$$E_\gamma = E_0 - E_R \quad (2.1)$$

The γ -ray is thus deficient in energy by a recoil kinetic energy. The recoil energy E_R , derived from the conservation of both energy and momentum, is given by

$$E_R = \frac{E_\gamma^2}{2Mc^2} \quad (2.2)$$

where c is the velocity of the light. The recoil energy depends on the mass of the nucleus and the energy of the γ -ray. For ^{57}Fe , the recoil energy of the 14.4keV transition is $\sim 2.0 \times 10^{-3}\text{eV}$ [35], which is far greater than the natural linewidth of this transition. Therefore, the energy loss resulted from the recoil in the γ -ray emission process will prevent the nuclear resonant absorption in another atom of the same kind by the reverse process.

The behavior of the recoiling atom, however, will be different when an atom is fixed in a *solid matrix*. In the Einstein model of a solid, the thermal properties of a lattice are described by the vibrational oscillations of the atoms with frequency ω [39]. The phonon energies are quantized ($E_R = \hbar\omega(n + \frac{1}{2})$), and transfer of energy

Figure 2.1: A schematic drawing of the nuclear resonant transitions between excited and ground states in two nuclei.

to the lattice can only take place in integral multiples of $\hbar\omega$ (i.e. $0, \pm\hbar\omega, \pm2\hbar\omega, \dots$). Thus the recoil energy can only be transferred to the lattice if it corresponds closely to an allowed quantum jump. If the recoil energy E_R is less than $\hbar\omega$, then either zero or one unit ($\hbar\omega$) of vibrational energy may be transferred to the lattice. It has been shown by Lipkin[40] that when many emission processes are considered, the average energy transferred to the lattice per emission of a γ -ray must exactly equal to the recoil energy E_R . Therefore there must be a certain probability that emission of a γ -ray results in no transfer of energy to the lattice (zero-phonon transitions). In a zero-phonon transition, the whole crystal rather than a single atom recoils, and this emission process is then effectively recoil-free. Hence the γ -ray emitted carries the total energy of the nuclear transition. When such a γ -ray strikes an identical atom in its ground state in a solid matrix, there is also a certain probability that the recoil-free resonant absorption may occur by the reverse process. This recoil-free emission and resonant absorption of γ -rays are the basis of the Mössbauer effect.

A Mössbauer spectrum is obtained as shown schematically in Fig. 2.2a. The γ -rays are emitted from a source containing the radioactive parent isotope ^{57}Co , as shown in Fig. 2.2b. ^{57}Co decays by electron capture to an excited state of Mössbauer isotope ^{57}Fe . This excited state subsequently passes to its ground state by recoil-free emission of the 14.4keV γ -ray used in the Mössbauer experiment. The γ -rays are shone through a sample (absorber) containing ^{57}Fe atoms in their ground state. The transmitted intensity of the γ -rays through the absorber is measured as a function of the γ -ray energy, which is varied by Doppler shifting the source with velocity v relative to the absorber. The small Doppler energy shifts of $E_D = E_\gamma v/c$ produced by this relative motion corresponds closely to the resolution of the γ -ray emitted by the source in a recoil-free Mössbauer event which is about 1 in 10^{12} . At γ -ray

Figure 2.2: a) Basic arrangement for measuring a Mössbauer spectrum in transmission geometry and b) nuclear decay scheme of ^{57}Co .

energies (appropriate v) that match the possible excitation energies in nuclei in the absorber, resonant absorption will occur, and an absorption “line” will be observed. It therefore follows that the Mössbauer spectrum is a record of the transmitted intensity of the γ -ray through an absorber as a function of the Doppler velocity v with respect to the source. This explains why the energy scale of the Mössbauer spectrum is given in mm/s and why energies are measured in mm/s in the Mössbauer experiments. As an example, the Mössbauer spectrum of α -Fe foil at 295 K is plotted in Fig. 2.3. The vertical scale of the Mössbauer spectrum is given in percent

Figure 2.3: Mössbauer spectrum for α -Fe foil at 295K.

transmission or percent absorption.

As mentioned in the beginning of this section, the natural linewidth of the 14.4 keV transition for ^{57}Fe is $\Gamma = 4.6 \times 10^{-9} \text{ eV}$ which is equivalent to 0.095 mm/s. However, in the actual Mössbauer experiments the smallest observable linewidth is twice as large as the natural linewidth because the spectrum is obtained as the convolution of the emission and absorption lines. Taking into account the source and instrumental broadening, the typical observed linewidth, defined by the full width at half-height of the Lorentzian peak, is about 0.25 mm/s. Because of the narrow observed linewidth, ^{57}Fe Mössbauer spectroscopy has a remarkably high relative resolution of 10^{-12} , the ratio of the linewidth to the transition energy. It should be pointed out that only relative energy or frequency changes between two resonating

nuclei can be measured with such an accuracy. The hyperfine interactions between electrons and nucleus discussed in section 2.2 are of order 10^{-8} eV and thus may be observed because of the high resolution of the γ -ray energy.

2.2 Hyperfine Interactions

The interactions between the Mössbauer nucleus and its surrounding environment are magnetic and electrostatic in nature and are known as hyperfine interactions. The three main interactions are the isomer shift, magnetic hyperfine interaction, and quadrupole interaction. Figure 2.4 shows the energy level diagram and resultant spectra for ^{57}Fe illustrating the origins of these interactions.

2.2.1 Isomer Shift

The isomer shift results from a change in the Coulombic interaction between the nuclear charges and electronic charge within the volume, which is caused by a difference in the size of the nucleus in its ground and excited states. The electronic charge density at the nucleus gives rise to energy shifts in the nuclear energy level by a small amount δE as illustrated in Fig. 2.4. Since the size of the nucleus in the excited state (R_e) is generally slightly different from the size of the nucleus in the ground state (R_g), the nuclear energy level shift δE will be different for the two nuclear states. As the size of the nucleus changes during its decay, the nuclear transition energy is shifted by an energy which is given by

$$\Delta E = (\delta E)_e - (\delta E)_g = \left(\frac{2\pi}{5}\right) Z e^2 |\Psi(0)|^2 (R_e^2 - R_g^2) \quad (2.3)$$

where Z is the nuclear charge, $|\Psi(0)|^2$ is the s-electron density at the nucleus. In a Mössbauer experiment, as the Mössbauer nucleus in the source and the absorber

Figure 2.4: Energy level diagram and resultant spectra for ^{57}Fe showing the origins of the isomer shift (δ), quadrupole splitting (Δ), magnetic dipole splitting, and combined magnetic dipole and quadrupole splitting. Each of vertical broken arrows represents a possible absorption line.

Figure 2.5: Mössbauer spectrum for a stainless steel foil at 295K.

are usually present in different chemical environments, the s -electron density at the nucleus in the source, $|\Psi|_S^2$, and the absorber, $|\Psi|_A^2$, have different values and so the nuclear energy level shift, ΔE , will be different. The difference in the shift between source and absorber can be expressed by

$$\delta = \Delta E_A - \Delta E_S = \left(\frac{2\pi}{5}\right) Z e^2 (R_e^2 - R_g^2) [|\Psi|_A^2 - |\Psi|_S^2] \quad (2.4)$$

This shift δ is generally called the isomer shift. In ^{57}Fe Mössbauer spectroscopy, the isomer shift of an absorber is given relative to a standard reference material, typically room temperature α -Fe which defines the zero of velocity. If the Mössbauer spectrum is a single line spectrum, the isomer shift appears as a shift of the absorption line from zero velocity as shown in Fig. 2.5 for a stainless steel foil.

2.2.2 Magnetic Hyperfine Interaction

The magnetic hyperfine interaction (nuclear Zeeman effect) arises from the coupling of the nuclear magnetic dipole moment μ with a magnetic field B at the nucleus and results in splitting of the nuclear ground and excited states if they have nuclear spin $I > 0$. The interaction can be formally expressed by the Hamiltonian

$$\mathcal{H} = -\mu \cdot B = -g\mu_N I \cdot B \quad (2.5)$$

where μ_N is the nuclear Bohr magneton ($eh/4\pi m_p = 5.04929 \times 10^{-27} \text{ JT}^{-1}$) and g is the nuclear Landé splitting factor ($g = \mu/I\mu_N$). Solving this Hamiltonian gives the eigenvalues

$$E_m = -\frac{\mu B}{I} m_I = -g\mu_N B m_I \quad (2.6)$$

here m_I is the magnetic quantum number and takes the values $I, I-1, \dots, -I$. It is obvious that the magnetic hyperfine interaction splits the nuclear state into $2I+1$ non-degenerate equally spaced sublevels with a separation of $\mu B/I$. The magnetic hyperfine splitting is illustrated in Fig. 2.4 for the isotope ^{57}Fe with the ground state ($I_g = 1/2$) and excited state ($I_e = 3/2$). Both states have magnetic dipole moments and are split by the magnetic interaction. Transitions between sublevels of the ground state and those of the excited state are subject to the selection rule: $\Delta m = 0, \pm 1$, for a magnetic dipole transition (as in ^{57}Fe). Therefore only six out of the eight possible transitions are allowed. A typical six-line Mössbauer spectrum for α -Fe foil is shown in Fig. 2.3. The relative intensities of the lines depend on the angle between the direction of the magnetic field at the nucleus and the propagation direction of the γ -ray (Table 2.1 [34]). Most samples for Mössbauer experiments are not oriented but consist of powder or polycrystalline materials in which to some approximation all values of θ are present with equal likelihood. For

Table 2.1: Angular dependence of the allowed transitions in a pure magnetic interaction (^{57}Fe). θ represents the angle between the direction of the magnetic field at the nucleus and the propagation direction of the γ -ray.

Transition	Δm	Angular dependence
$\pm\frac{3}{2} \rightarrow \pm\frac{1}{2}$	± 1	$\frac{3}{4}(1 + \cos^2 \theta)$
$\pm\frac{1}{2} \rightarrow \pm\frac{1}{2}$	0	$\sin^2 \theta$
$\mp\frac{1}{2} \rightarrow \pm\frac{1}{2}$	∓ 1	$\frac{1}{4}(1 + \cos^2 \theta)$

such samples, the relative transitions intensities are obtained by integration over a sphere, the relative intensities of the six lines are in a 3:2:1:1:2:3 ratio; this is the origin of the intensity pattern seen in Fig. 2.3.

One important piece of information obtained from a sextet spectrum is the overall splitting which is proportional to the magnetic field experienced by the nucleus below the Curie temperature of a ferromagnetic material. This magnetic field is usually referred to as the internal hyperfine field B_{hf} or effective magnetic field B_{eff} . In the case of α -Fe, the room temperature splitting between the two outermost lines is 10.6mm/s , which corresponds to a hyperfine field of 33 T at the nucleus. This value is generally used to define the velocity scale of the Mössbauer spectrum. The internal hyperfine field B_{hf} at a Fe nucleus has several contributions and can be described by

$$B_{hf} = B_{ext} + B_{fci} + B_o + B_L \quad (2.7)$$

where B_{ext} is an applied external field, B_{fci} represents the Fermi contact interaction, B_o the orbital contribution and B_L the local field. The Fermi contact interaction arises from the finite electron spin density at the nucleus. The spin density may arise from the localized s-electrons and from the conduction electrons. Because of the spin polarization of the s-electrons by the partly filled 3d or 4f shell (in the case of Fe

or rare earth), a different electron density for the spin-up and spin-down electrons exists at the nucleus, and there will be a net spin polarization. The interaction of this electron spin polarization with the nucleus is called the Fermi contact interaction and can be considered as an effective magnetic field at the nucleus. The orbital contribution B_o to the hyperfine field is produced by the orbital angular momentum of the $4f$ (or $5f$) electrons. For most rare earth atoms [41] this component of the hyperfine field is proportional to the magnetic moment of the atom. However, B_o is zero for atoms with closed or half-filled shells with spherical symmetry. The local field B_L includes mainly the contributions of the magnetic dipole field and the anisotropy field to the hyperfine field. The magnetic dipole field at the nuclear site is due to the coupling between the spins of the parent atom and its neighbors. The anisotropy field is produced by the dipole moment of the asymmetric charge distribution of the $3d$ -electrons.

Figure 2.6 shows an example of a more complex Mössbauer spectrum observed for $\text{Nd}_2\text{Fe}_{14}\text{B}$. In compounds where iron atoms are present on more than one crystallographically, the different sites may often be distinguished as different sextets in the Mössbauer spectrum. The relative absorption area of each sextet is proportional to the relative iron populations of the crystallographic sites. In $\text{Nd}_2\text{Fe}_{14}\text{B}$, for instance, there are six crystallographically distinct iron sites in the crystal structure. The observed Mössbauer spectrum of $\text{Nd}_2\text{Fe}_{14}\text{B}$, therefore, is the superposition of six sextets with the intensity ratio of 16:16:8:8:4:4 corresponding to the relative iron populations of the six sites k_1 , k_2 , j_1 , j_2 , e , and c .

Figure 2.6: Mössbauer spectrum of $\text{Nd}_2\text{Fe}_{14}\text{B}$ at 295K.

2.2.3 Quadrupole Interaction

The electric quadrupole moment (eQ) is a measure of the deviation from spherical symmetry of the nuclear charge distribution. An asymmetric distribution of the charges surrounding the Mössbauer nucleus results in an inhomogeneous electric field described by the electric field gradient at the nucleus. The interaction between the electric quadrupole moment and the electric field gradient, which is called the quadrupole interaction, lifts partly the degeneracy of nuclear levels for $I > 1/2$ as shown in Fig. 2.4. This interaction can be expressed by a Hamiltonian of the form [42]:

$$\mathcal{H} = \frac{eQV_{zz}}{4I(2I-1)} \left[3\hat{I}_z^2 - \hat{I}^2 + \eta(\hat{I}_+^2 + \hat{I}_-^2/2) \right] \quad (2.8)$$

where I is the nuclear spin quantum number, $\hat{I}$ is the nuclear spin operator, $\hat{I}_{\pm} = \hat{I}_x \pm i\hat{I}_y$ are the raising and lowering operators, $\hat{I}_x$, $\hat{I}_y$, and $\hat{I}_z$ are the nuclear spin component operators, $\eta = (V_{xx} - V_{yy})/V_{zz}$ is the asymmetry parameter of the electric field gradient tensor, and V_{zz} is the principal component of the electric field gradient tensor at the nucleus. Using first-order perturbation theory, the eigenvalues of $\mathcal{H}$ can be found as

$$E_Q = \frac{eQV_{zz}}{4I(2I-1)} [3m_I^2 - I(I+1)] (1 + \eta^2/3) \quad (2.9)$$

here, $m_I = I, I-1, \dots, -I$ is the nuclear magnetic spin quantum number.

It is clear from the expression of E_Q that the effect of the electric quadrupole interaction will split a nuclear state with $I > 1/2$ into substates $|I, \pm m_I\rangle$ without shifting the center of gravity. For example, in the case of ^{57}Fe nucleus the nuclear ground state ($I = 1/2$) is unsplit, and the excited state ($I = 3/2$) is split into two doubly degenerate substates $|3/2, \pm 3/2\rangle$ and $|3/2, \pm 1/2\rangle$ separated by

$$\Delta = \frac{eQV_{zz}}{2} (1 + \eta^2/3)^{1/2} \quad (2.10)$$

In a Mössbauer experiment, transitions between the ground state and both substates $|I, \pm m_I\rangle$ with $I = 3/2$ can take place according to the selection rule $\Delta m_I = 0, \pm 1$. Using a single-line source, one would observe two resonant absorption lines with equal intensities for a randomly oriented polycrystalline material in the Mössbauer spectrum as illustrated in Fig. 2.4. The separation between the two lines corresponds to the quadrupole splitting Δ .

2.2.4 Combined Quadrupole and Magnetic Hyperfine Interaction

Both the magnetic and quadrupole hyperfine interactions express a directional interaction of the nucleus with its environment. However, when the two are present

Figure 2.7: Orientation of the magnetic hyperfine field in the axes of the electric field gradient tensor.

together, their respective principal axes are not necessarily parallel.

Figure 2.7 gives the orientation of the magnetic hyperfine field relative to the principal axes of the electric field gradient tensor. If the quadrupole interaction can be treated as a small perturbation on the magnetic interaction, then the resultant energy levels for the Hamiltonian expressed in equation 2.5 are given by

$$E_m = -g\mu_N B m_I + (-1)^{|m_I|+\frac{1}{2}} \frac{eQV_{zz}}{4} \left(\frac{3\cos^2\theta - 1}{2} \right) \quad (2.11)$$

where θ is the angle between the magnetic axis and the major axis (V_{zz}) of the electric field gradient tensor. Therefore all the magnetic hyperfine lines are shifted by a quantity

$$\Delta E_{m_I} = (-1)^{|m_I|+\frac{1}{2}} \frac{eQV_{zz}}{4} \left(\frac{3\cos^2\theta - 1}{2} \right) \quad (2.12)$$

From this equation, it is easy to find out the difference in the splitting between line 1 and 2 and the splitting between line 5 and 6 in a sextet as shown in Fig. 2.4. This difference is referred to as the quadrupole shift and is given by

$$\epsilon = \frac{eQV_{zz}}{2}(3\cos^2\theta - 1) \quad (2.13)$$

Thus, in the presence of both the quadrupole and magnetic interactions, the splittings between the nuclear excited state sublevels are no longer equal and the absorption lines are not equally spaced in energy as illustrated in the lower diagram of Fig. 2.4. The presence of a small quadrupole perturbation is easily visible because the spectrum is no longer symmetrical about the centroid.

2.3 Analysis of Mössbauer Spectra

Mössbauer spectra of R-Fe based compounds are very complex because of their complex crystal structures. They usually consist of a number of subspectra which result from different crystallographic iron sites in the structure. A further complication is caused by the combined quadrupole and magnetic hyperfine interaction as the materials are in a magnetically ordered state. Generally speaking, an observed Mössbauer spectrum may be decomposed into individual subspectra associated with crystallographic sites, each with its own hyperfine parameters. The relative intensities of the subspectra are constrained to the crystallographic populations of the sites. However, the vector character of the hyperfine and the tensor character of the electric field gradient may cause a magnetic inequivalence of crystallographically equivalent sites. Thus, a further magnetic subsplitting of the subspectra may be needed to account for these magnetically inequivalent sites.

As described in section 2.2.4, the quadrupole shift can be written as

$$\epsilon = \frac{eQV_{zz}}{2}(3\cos^2\theta - 1)$$

where θ is the angle between the magnetization direction and the principal axis, V_{zz} , of the electric field gradient tensor. It has been shown that when the magnetization lies in the basal plane, which is the case for all of R_2Fe_{17} compound at room temperature, both quadrupole splitting and hyperfine field need not have a single value among the crystallographically equivalent sites. In other words, a group of crystallographically equivalent sites are not *magnetically* equivalent. As a result, they will split into several groups with different hyperfine parameters. To illustrate such magnetic inequivalence of the crystallographic sites, the best example is the cubic Laves phase RFe_2 compounds [43,44]. In these compounds, all four iron atoms occupy crystallographically equivalent sites of trigonal ($3\bar{m}$) symmetry on the four $[111]$ axes. As a result, there are four different local principal electric field gradient axis systems for the Fe atoms, with V_{zz} along their respective three fold rotation. Depending on the direction of magnetization, the iron atoms may or may not be magnetically equivalent. For example, for the magnetization direction along any one of the $[100]$ directions, only a single sextet Mössbauer spectrum is observed because all Fe atoms are characterized by a single value of θ . However, for a $[111]$ direction of magnetization, three out of four iron atoms have $\theta=70.32$ and one has $\theta=0$. As a result, the Mössbauer spectrum splits into two distinct subspectra whose intensities are in the ratio of 3:1. This is found to be the case in $TbFe_2$ as the Mössbauer spectrum in Fig. 2.8 shows.

A typical procedure for fitting a Mössbauer spectrum is to obtain a first estimate (*i.e.* starting values) of the hyperfine parameters for various subspectra. These starting values can be calculated from the line positions in the magnetic Mössbauer

Figure 2.8: Mössbauer spectrum of TbFe_2 at 77 K. The solid line is the calculated spectrum with the magnetically subsplitting of the crystallographically equivalent sites (After [43]).

spectra if the six line positions are well resolved or taken from published sources, if any. The starting values are then used to compute a theoretical spectrum and refined to give the best fit to the experimental spectrum with a computer program based on a nonlinear least-squares minimization method. The parameters used in fitting include baseline, linewidth, and total absorption plus the isomer shift, quadrupole splitting, and hyperfine field for each subspectrum. The relative intensities of the subspectra are constrained according to the relative populations of the crystallographic sites in the crystal structure.

Chapter 3

Experimental Methods

3.1 Sample Preparation and Characterization

3.1.1 Sample Preparation

Reference samples (*cobalt-free*) were obtained by rf-induction melting appropriate amounts of 99.9% pure elements on a water-cooled copper boat under Ti-gettered argon. To ensure homogeneity all samples were melted up to five times. As-made ingots wrapped in Ta-foil were sealed into quartz tubes evacuated to $\sim 10^{-6}$ mbar and annealed for about 2 weeks at 1173 K or higher. The annealing treatment is essential for preparing single phase alloys of $\text{Nd}_2\text{Fe}_{17}$ and ThFe_5 . In the case of $\text{Nd}_2\text{Fe}_{17}$, the as-made alloys contained a large amount of α -Fe. After heat treatment, essentially α -Fe free $\text{Nd}_2\text{Fe}_{17}$ alloys were obtained. For ThFe_5 alloys, the as-made ingots were found to contain mainly the $\text{Th}_2\text{Fe}_{17}$, ThFe_3 and Th_2Fe_7 phases. Only a small fraction of ThFe_5 was present in the as-made alloys. Samples with a majority of the ThFe_5 phase were obtained only after annealing at about 1430K for two weeks followed by quenching in water [45]. Quenching of the samples is necessary because ThFe_5 is unstable at low temperatures and decomposes into the adjacent phases Th_2Fe_7 and $\text{Th}_2\text{Fe}_{17}$ when cooled slowly to room temperature.

Source samples (^{57}Co doped) were prepared by incorporating the radioisotope ^{57}Co ($\sim 1\text{ppm}$) into iron metal prior to alloying with the other elements. 37 MBq ^{57}Co is supplied as cobalt chloride ($^{57}\text{CoCl}_2$) in 0.5M hydrochloric acid (HCl) by New England Nuclear Medical Products [46]. $^{57}\text{CoCl}_2$ was neutralized with NH_4OH and evaporated to dryness in an oven at about 80 °C. ^{57}Co , deposited in the bottom of the container, was then mixed with ~ 150 mg of $^{56}\text{Fe}_2\text{O}_3$ (corresponds to about 100 mg ^{56}Fe). Here ^{56}Fe rather than natural iron is used to prevent loss of signal from resonant self-absorption by the ^{57}Fe (2.17 at.%) present in natural iron. A few drops of distilled water were added into the container to form a uniform mixture of ^{57}Co and $^{56}\text{Fe}_2\text{O}_3$. Once again, the mixture was dried at about 80 °C in the oven. The mixture was then transferred into a Ni-boat and reduced to the metallic state by annealing at 900 °C under flowing H_2 for about 2 hours. Finally, the radioactive iron metals (containing ~ 27 MBq ^{57}Co) and appropriate amounts of other elements were pressed into a pellet with a typical mass of ~ 150 mg. The reason for using small sample mass is because (i) the limited range of the 14.4 keV γ -ray requires the use of thin sources (about 50mg samples were used in the measurements); and (ii) the cost of using both ^{57}Co and ^{56}Fe materials is very high ($\sim \$500/\text{sample}$). The small pellet was melted under argon in a miniature rf-induction melter, which was specially constructed to alloy the small amounts of samples and to be operated inside a glove box. The melter consisted of a double layer spiral rf-induction coil and a boron-nitride boat sealed inside a quartz tube. The as-made ingots were annealed under the same conditions as their corresponding reference samples.

3.1.2 Characterization

X-ray powder diffraction has been widely used in structural characterization and is a powerful tool in identifying crystalline phases in a polycrystalline material. The x-ray diffractometer used in this study is an automated Nicolet-Stöe L11 powder diffractometer with CuK_α radiation ($\lambda = 1.5418 \text{ \AA}$). All x-ray diffraction measurements were done in the reflection mode. The pulverized samples were fixed on a thin glass slide using a double sided adhesive tape. For the source samples, the powders were fixed between two adhesive tapes to avoid possible contamination from the radioactive materials. An example of an x-ray diffraction pattern for $\text{Dy}_2\text{Fe}_{17}$ is shown in Fig. 3.1a.

In contrast to x-ray diffraction, thermomagnetic analysis (TMA) is a relatively new technique to be used in analysis of crystalline phases and it is only capable of detecting magnetic phases in the materials [47]. However its high sensitivity and efficiency make it very useful in determination of extremely small amounts of magnetic phases present in a sample which may not be detectable with x-ray diffraction. TMA used in this work is a Perkin-Elmer TGA-7 which is made up of two essential components: an ultramicrobalance and a furnace element. We apply a small field gradient at the location of the sample. When a magnetic sample lies in a magnetic field gradient, magnetic forces are exerted on the sample and are proportional to the magnetization of the magnetic phase or phases present in the sample. The magnetic forces are measured by the ultramicrobalance. The sample is heated with a uniform heating rate and a sharp drop in the magnetic forces at $T=T_c$ easily identifies the different magnetic phases present in the sample. Samples used in TGA measurements can be of any shape with a mass of as small as 0.1 mg. In the present work, small pieces of ingots were used in the TGA measurements.

Figure 3.1: (a) X-ray diffraction pattern for $\text{Dy}_2\text{Fe}_{17}$ and (b) TGA curve for as-made sample of ThFe_5 , which shows clearly the multi-phase nature of as-made alloy.

The measurements were made at temperatures from 295K to 1123K (typical heating rate 40K/min) under a constant flow of purified Argon gas. In the case of source samples, the samples were wrapped in an aluminium pan to avoid contamination from the radioactive materials. Fig. 3.1b shows an example of TGA curve for the as-made sample of ThFe_5 . The multi-phase nature of this sample is clearly seen in this figure.

3.2 Mössbauer Experiments

The Mössbauer experiments were carried out on a conventional constant-acceleration spectrometer. The Mössbauer spectrometer in transmission geometry is illustrated schematically in Fig. 3.2. The major part of this spectrometer is the EG&G Ortec ACE-MCS system (multichannel analyzer) installed in an IBM PC which can store an accumulated total of γ -ray counts in each of several hundred individual registers known as channels. The analyzer is synchronized with the drive so that each channel corresponds to a particular drive velocity. Thus, the channel number corresponds to the Doppler-shifted γ -ray energy, and the channel contents corresponds to the number of γ -rays transmitted through the absorber at that energy. The source is moved relative to the absorber by the electromagnetic Mössbauer velocity transducer. A triangular voltage waveform with $f = 23$ Hz supplied by a digital function generator is used to produce a constant-acceleration in which the drive shaft and the source spend equal time intervals at each velocity increment. The electromagnetic Mössbauer velocity transducer and the Mössbauer driving unit used in this work are supplied by WISSEL in Germany. The γ -ray detection system is a conventional gas proportional counter. The pulses from the detector are pre-amplified and then amplified, passed through a discriminator called a single channel analyzer (SCA)

Figure 3.2: A schematic diagram of a Mössbauer spectrometer in transmission geometry.

which rejects most of the non-resonant background radiation, and finally are fed to the appropriate channels. The whole Mössbauer spectrum is accumulated by repetitively scanning the whole velocity range required. A typical counting time for a transmission spectrum is about two days.

I. Reference Spectrum

The Mössbauer spectra for reference samples were obtained in standard transmission method with a 1 GBq $^{57}\text{CoRh}$ single line source and a proportional counter filled with a mixture of Xenon and 4% CO₂ gas at 1 atmosphere. The detector is operated at a voltage of about 1700 V. A dewar with a cold-finger was used to obtain spectra at liquid nitrogen temperature (77K).

Absorbers/samples are typically a thin layer of powdered materials which are a mixture of ~ 80 mg powdered alloy and some boron nitride powder. The boron nitride is used to aid the dispersion. The powder materials, about 1mm in thickness and 150mm² in area, are held in place by two sheets of Kapton epoxied to the sample holder.

II. Source Spectrum

The room temperature Mössbauer spectra for source samples could be obtained using standard transmission method with a single line absorber and a conventional proportional counter despite the extremely low signal-to-noise ratio of this arrangement. A typical single line absorber is a thin foil of 310 stainless steel enriched in ^{57}Fe . When the Mössbauer source measurements are needed to be made at low temperatures, however, this method is hardly applicable because in this case the detector has to be mounted on a conventional Mössbauer drive so that the source can be placed in a cryostat. Obviously, the conventional proportional counter usually used in the transmission methods is not suitable for this purpose. An alternative method to this is the conversion electron Mössbauer spectroscopy in the scattering geometry where the conversion electron detector could be constructed with a mass less than 30 g [48]. For the Mössbauer source measurements, we constructed a resonant conversion electron detector with a mass of $\sim 25\text{g}$, utilizing 90% ^{57}Fe enriched stainless steel foil. This lightweight detector not only allows low temperature source measurements to be made, but also yields a more than six-fold enhancement in signal-to-noise ratio over conventional transmission methods. A detailed description of this detector will be given in section 3.3. All the source spectra were obtained using this conversion electron detector. The typical counting time for each spectrum

is about two weeks which is half of the time needed for conventional transmission method. When Mössbauer measurement at a reduced temperature was required, the detector, instead of the source, was mounted on the Mössbauer drive and the source sample was placed in a cryostat.

Similar to the preparation of an absorber for the reference, sources/samples were prepared from finely ground powder spread into a thin layer in a 20 mm diameter holder. The thin layer is roughly $20\mu\text{m}$ in thickness, about one absorption depth of 14.4 keV photons in iron[49] and held in place by a sheet of kapton epoxied to the sample holder.

III. Fitting of the Spectra

All reference spectra were fitted using the method discussed in section 2.3 with a standard nonlinear least-squares minimization routine written by M. Sutton and D. H. Ryan. In general, a reference spectrum is decomposed into individual subspectra for the number of crystallographically inequivalent iron sites. The adjustable parameters, besides the common baseline and linewidth, include isomer, quadrupole splitting, and hyperfine field for each subspectrum. The relative intensities of the subspectra are constrained to the multiplicities of the crystallographic iron sites. Only one adjustable parameter for the intensities of the subspectra is included in the fitting process. In the event that the magnetic inequivalence of crystallographically equivalent sites arises from the magnetization being in the basal plane or other particular direction, the subspectrum associated with such site is further split into several sextets according to the number of magnetically inequivalent sites. In this instance, the isomer shift is kept same for all the magnetically split subspectra while the quadrupole splitting and hyperfine field are allowed to be adjustable. It should

be emphasized that the differences among quadrupole splittings of the magnetic subspectrum should be consistent with the relationship expressed by the equation 2.13 where the value of $\frac{eQV_{zz}}{2}$ is the same for all these subspectra.

All source spectra were simply fitted using the best-fit parameters obtained from the reference spectra by allowing only the off-resonance baseline, linewidth, and intensities of the individual subspectra to vary. As we have mentioned in the introduction of this thesis, the requirement that the subspectrum parameters of the reference sample must fit the source spectrum with changes only in the intensities imposes a very severe constraint on the fit and provides a consistency check on the parameters used for the reference spectrum.

3.3 Conversion Electron Detector

As mentioned briefly in the preceding section, the conversion electron Mössbauer spectroscopy is used in our Mössbauer source experiments. The key component of this technique is the conversion electron detector. We have designed and constructed a conversion electron detector to fulfill the requirements of the low temperature Mössbauer source measurements and to enhance the counting efficiency of these experiments. Before going to the detailed descriptions of this detector, we will briefly describe the decay process of the excited ^{57}Fe nuclei after resonant absorption of the 14.4 keV γ -rays and the simple design of a normal conversion electron detector. Figure 3.3 shows schematically the decay process of the 14.4 keV excited state in ^{57}Fe . Following resonant absorption of the 14.4 keV γ -rays by ^{57}Fe , 91% of the excited nuclei return to the ground state by conversion electron emission, of which 81% are *K* electrons with an energy of 7.3 keV (Table 3.1). Only 9% of the nuclei return to the ground state by re-emitting a 14.4 keV γ -ray. Approximately 70% of

Figure 3.3: A schematic diagram of internal conversion process for the 14.4 keV transition of ^{57}Fe .

the atoms that are ionized as a result of K conversion subsequently release energy by the emission of 5.4 keV KLL Auger electrons, and the remaining 30% undergo de-excitation by emission of 6.4 keV K_{α} x-rays. Almost two conversion electrons are emitted, on average, for each resonant absorption. The relatively low energy electrons (~ 6 keV) are generally detected by constructing a proportional counter around the sample: the (grounded) sample forms the cathode and one or more fine wires biased to ~ 1 kV form the anode plane. The usual fill gas is helium, to minimize sensitivity to γ -rays, with a few percent methane added as quench gas.

Low counting efficiency is the major problem of a normal conversion electron detector (CED). Primarily two factors limit the performance: (i) the escape depth of the conversion electrons is small (~ 100 nm) compared to the penetration depth of the 14.4 keV γ -ray (~ 13 μ m in iron) and thus only a small fraction of the resonant material in a normal sample is actually counted; (ii) all of the incident radiation can generate photoelectrons from the sample leading to a non-resonant background rate. Efficiency may be maximized by making the resonant foils so thin that essentially all of the conversion electrons produced escape to be detected. A sufficient number of such foils and anode planes may be placed in sequence so as to fully absorb the

Table 3.1: Radiation emitted after resonant absorption of the 14.4 keV by ^{57}Fe [50].

<i>Radiation</i>	<i>Energy (keV)</i>	<i>Probability</i>
γ -ray	14.4	0.09
K electron	7.3	0.81
L electron	13.6	0.09
M electron	14.3	0.01
K x-ray	6.4	0.24
KLL Auger electron	5.4	0.57

incident radiation. This device is a microfoil conversion electron (MICE) detector [51,52]. For ^{57}Fe , the optimum foil thickness is about 300nm . Stainless steel is generally used as it gives a single line absorber and it is usually prepared from iron enriched to about 90% in ^{57}Fe in order to maximize the resonant cross section and minimize the amount of non-resonant material in the detector. Two such foils are required. Despite the technical difficulties associated with their construction, such detectors have been used and greatly enhance the signal-to-noise ratio, yielding a factor of ten increase in efficiency over the conventional proportional counter and absorber arrangement [51]. Recently, a lightweight design was reported which can be mounted on a velocity transducer [53].

Most of the difficulties in constructing and operating a MICE detector are associated with the extremely thin foils. As they are not commercially available they must be rolled from thicker stock, moreover they are fragile once made. Great care must be taken in mounting the foils in order to minimize vibrations which will otherwise cause line broadening. It is not practical, therefore, to construct and use a MICE detector in our work. This led us to investigate a simpler design which retains most of the advantages of microfoils detectors but uses only commercially available parts, greatly simplifying the construction and reducing cost. In the following subsections, we describe a vibration-free version of a such detector. The detector has a mass of $\sim 25\text{ g}$ allowing it to be driven in constant-acceleration mode by a conventional Mössbauer drive, without limiting velocity range.

3.3.1 Detector Description

Fig. 3.4 shows the cross section of the detector. The detector body, made of plexiglass, consists of three parts: (i) front window, (ii) anode wire housing and (iii) back

Figure 3.4: Sectional views of the detector. Top diagram illustrates a section through the anode plane and the bottom one shows a side view of the separated components.

plate. The front window is a 0.12 mm aluminised mylar sheet epoxied to a plexi-glass plate 40 mm in diameter, 2 mm thick with a 20 mm diameter aperture in the center. The $25\text{ }\mu\text{m}$ gold-coated tungsten anode wire is supported in the center of the detector by 1.4 mm o.d. copper capillaries epoxied into holes drilled in the detector body. These tubes are equidistant from the central axis and are 5 mm apart. The end wires of the anode are soldered to the tubes. This anode configuration provides a large active detector volume. A $1.3\text{ }\mu\text{m}$ 310 stainless steel foil 90% enriched in

^{57}Fe [46], is cemented to the aluminised rear side of the detector with a conducting adhesive which keeps the foil firmly fixed and maintains good electrical contact with the grounded inner body of the detector. Facing surfaces were polished so as to achieve good contact but not a hermetic seal. Finally all three parts are held together with four brass bolts. The interior space is a 20 mm diameter cylinder 8 mm in height. All inner surfaces of the detector are fully aluminised and connected to ground. A 250 mm long, 2.5 mm o.d. lightweight coaxial cable (RG-174/u) between the detector and preamplifier is used to minimize mechanical stiffness which would interfere with driving the detector. The gas enters through a 2 mm od plastic tube, and exits between the joints in the detector parts. A constant gas flow is used to prevent air leaking back into the active region. All possible measures have been taken in order to reduce the mass of the detector, which could affect the linearity of the acceleration when the detector is mounted on the drive. The present detector has a total mass of ~ 25 g.

The detector is operated as a conventional continuous-flow gas-filled proportional counter using pre-mixed helium/4% methane at a flow rate of $40 \text{ cm}^3/\text{min}$ (chosen to optimise counting efficiency). Too low a flow rate leads to air getting into the detector resulting in a significant loss of efficiency. The operating voltage was determined by observing the amplifier output and counting rate as the bias voltage was increased from 800 V to 1200 V in 50 V steps. In our case, the operating voltage was found to be 1050 V. Lower voltages yield reduced gain making operation difficult, while some breakdown was observed at higher voltages. Some background contributions are always present. One is due to detector noise and low energy photoelectrons which can be reduced by optimising the lower level discriminator setting (about channel 30 on Fig. 3.5 was used). Another is due to photoelectrons produced

Figure 3.5: Pulse height spectrum obtained using a 74 MBq ^{57}Co source with the conversion electron detector (a) on resonance, and (b) off resonance.

by incident 6.5 keV Fe K_{α} x-rays from the source. These may be reduced using a 1.7 mm plexiglass filter in front of the source, although at the expense of a slightly reduced count rate. The remaining background of photoelectrons comes from non-resonant 14.4 keV photons and higher energy photons (122 keV and 136 keV) from the source which are scattered by non-resonant materials (e.g. in the stainless steel, detector body and wires) in the detector. This latter contribution is minimized by using low-Z materials as far as possible.

3.3.2 Detector Performance

Figure 3.5 shows the pulse height spectrum obtained with 74 MBq $^{57}\text{CoRh}$ source on and off resonance. Background events were minimized by setting the lower level discriminator to approximately channel 30. In Fig. 3.6 we compare the Mössbauer spectra obtained using the conversion electron detector with a transmission spectrum

Figure 3.6: Mössbauer spectra of 310 stainless steel (a) measured using the conversion electron detector (CED) and (b) measured in transmission using an $8\mu\text{m}$ 310 stainless steel foil. A substantial improvement in the signal-to-noise ratio of the CED spectrum is apparent. Both spectra were measured in the same geometry for the same time.

Table 3.2: Summary of conversion electron detector (CED) performance compared with standard transmission measurement (TRANS) on a $8\mu\text{m}$ 310 stainless steel foil. All spectra were recorded for the same time and in identical geometry. The numbers in brackets are the fraction of incident photons leading to the signal; in the case of the CED background the fraction is over estimated by a factor of ten as the contributions of the 122 keV and 136 keV γ -rays are not included in the incident beam measurement.

	Baseline (counts)	Signal (counts)	Linewidth (mm/s)	Effect (%)	Signal/Noise
Incident beam	27732	-	-	-	-
CED	459 (1.7%)	3082 (11%)	0.16	671	144
TRANS	21904 (79%)	3312 (12%)	0.19	15	22

obtained for the same counting time and geometry using an $8\mu\text{m}$ 310 stainless steel absorber prepared from natural iron. For fixed counting time and geometry, we obtained more than a six-fold increase in signal-to-noise ratio using the conversion electron detector compared with the standard transmission measurement, and the linewidth (HWHM) is also reduced: $0.16(1)\text{ mm/s}$ compared with $0.19(1)\text{ mm/s}$ from the transmission spectrum.

This latter change is primarily due to the reduction of saturation effects. The performance of the detector is summarized in Table 3.2. We note that the primary source of improvement in this detector design is background reduction, as the detected signal strength is the same for both transmission and conversion electron detection. Microfoil systems which allow signal detection from both faces of several foils yield essentially the same background suppression with approximately double the counting efficiency. Even though our simplified design only allows detection of

electrons from a single face of the foil, we still obtain a factor of six enhancement in signal-to-noise ratio over the transmission measurement, indicating that much of the complexity of MICE systems can be avoided for ^{57}Fe measurements.

Chapter 4

Results and Discussion

This chapter presents and discusses the results of cobalt site preferences in the compounds $\text{Nd}_2\text{Fe}_{14}\text{B}$, $\text{Nd}_2\text{Fe}_{17}$, $\text{Gd}_2\text{Fe}_{17}$, $\text{Dy}_2\text{Fe}_{17}$, ThFe_5 , $\text{Er}_8\text{Fe}_{23}$, and DyFe_3 . The crystallographic data of the compounds investigated are summarized in Table 4.1. Mössbauer spectra and observed Co site preferences in these compounds are presented in section 4.1. The results will be analyzed in terms of near-neighbor environment and Wigner-Seitz cell volume for each site based on a Wigner-Seitz analysis of the crystal structure in section 4.2.

4.1 Mössbauer Spectra and Site Preferences

4.1.1 $\text{Nd}_2\text{Fe}_{14}\text{B}$

Figure 4.1 shows the x-ray diffraction pattern and TGA curve of the reference sample for $\text{Nd}_2\text{Fe}_{14}\text{B}$. X-ray diffraction and TGA results confirm that both the reference and source samples of $\text{Nd}_2\text{Fe}_{14}\text{B}$ consist of tetragonal $P4_2/mnm$ -phase $\text{Nd}_2\text{Fe}_{14}\text{B}$. The reference sample contained $\sim 2\%$ $\text{Nd}_{1.1}\text{Fe}_4\text{B}_4$. No impurity phase was detected in the source sample. The Curie temperature (T_c) of the reference and source samples were found to be 585K.

Figure 4.2 shows the room temperature Mössbauer spectrum of the reference

Table 4.1: Crystallographic data for R-Fe based compounds. Included are structure type, lattice constants, space group, atomic sites (multiplicity and Wyckoff notation), and nuclear coordinates x, y, z (in units of the lattice constants) [54,55]

Compound	Structure type and lattice constants (Å)	Space group	Atom	Point symmetry	Atomic positions
Nd ₂ Fe ₁₄ B	Tetragonal Nd ₂ Fe ₁₄ B a = 8.800 c = 12.200	P4 ₂ /mmm No. 136	Fe(4c)	mm	(0.500, 0.500, 0.114)
			Fe(4c)	2/m	(0.000, 0.500, 0.000)
			Fe(8j ₁)	m	(0.098, 0.098, 0.204)
			Fe(8j ₂)	m	(0.317, 0.317, 0.246)
			Fe(16k ₁)	1	(0.223, 0.567, 0.127)
			Fe(16k ₂)	1	(0.037, 0.360, 0.176)
			Nd(4f)	mm	(0.268, 0.268, 0.000)
			Nd(4g)	mm	(0.140, -0.140, 0.00)
			B(4g)	mm	(0.371, -0.371, 0.00)
Nd ₂ Fe ₁₇	Rhombohedral Th ₂ Zn ₁₇ a = 8.578 c = 12.462	R3m No. 166	Fe(6c)	3m	(0.000, 0.000, 0.096)
			Fe(9d)	2/m	(0.500, 0.000, 0.500)
			Fe(18f)	2	(9.286, 0.000, 0.000)
			Fe(18h)	m	(0.500, 0.500, 0.148)
			Nd(6c)	3m	(0.000, 0.000, 0.333)
Gd ₂ Fe ₁₇	Hexagonal Ni ₁₇ Th ₂ a = 8.496 c = 8.345	P6 ₃ /mmc No. 194	Fe(4f)	3m	(0.333, 0.667, 0.105)
			Fe(6g)	2/m	(0.500, 0.000, 0.000)
			Fe(12j)	m	(0.333, 0.969, 0.250)
			Fe(12k)	m	(0.167, 0.333, 0.985)
			Gd(2h)	$\bar{6}m2$	(0.000, 0.000, 0.250)
			Gd(2d)	$\bar{6}m2$	(0.333, 0.667, 0.750)
Dy ₂ Fe ₁₇	Hexagonal Ni ₁₇ Th ₂ a = 8.448 c = 8.295	P6 ₃ /mmc No. 194	Fe(4f)	3m	(0.333, 0.667, 0.105)
			Fe(6g)	2/m	(0.500, 0.000, 0.000)
			Fe(12j)	m	(0.333, 0.969, 0.250)
			Fe(12k)	m	(0.167, 0.333, 0.985)
			Dy(2b)	$\bar{6}m2$	(0.000, 0.000, 0.250)
			Dy(2d)	$\bar{6}m2$	(0.333, 0.667, 0.750)
ThFe ₈	Hexagonal CaCu ₈ a = 5.116 c = 4.046	P6/mmm No. 191	Fe(2c)	$\bar{6}m2$	(0.333, 0.667, 0.000)
			Fe(3g)	mmm	(0.500, 0.000, 0.500)
			Th(1a)	6/mmm	(0.000, 0.000, 0.000)
Er ₆ Fe ₂₃	Cubic Th ₆ Mn ₂₃ a = 12.005	Fm3m No. 225	Fe(4b)	m3m	(0.500, 0.500, 0.500)
			Fe(24d)	mmm	(0.000, 0.250, 0.250)
			Fe(32f ₁)	3m	(0.178, 0.178, 0.178)
			Fe(32f ₂)	3m	(0.378, 0.378, 0.378)
			Er(24e)	m	(0.203, 0.000, 0.000)
DyFe ₃	Rhombohedral PuNi ₃ a = 5.123 c = 24.570	R3m No. 166	Fe(3b)	3m	(0.000, 0.000, 0.500)
			Fe(6c)	3m	(0.000, 0.900, 0.334)
			Fe(18h)	m	(0.500, 0.500, 0.083)
			Dy(3a)	$\bar{3}m$	(0.000, 0.000, 0.000)
			Dy(6c)	3m	(0.000, 0.000, 0.141)

Figure 4.1: X-ray diffraction pattern and TGA curve for the reference sample of $\text{Nd}_2\text{Fe}_{14}\text{B}$.

Figure 4.2: Room temperature Mössbauer spectrum of the reference for Nd₂Fe₁₄B. The theoretical spectrum is shown as the solid line through the data points.

sample for $\text{Nd}_2\text{Fe}_{14}\text{B}$. Before the site occupancies of cobalt can be obtained, a reliable fit for the reference spectrum must be found. There are six crystallographically distinct iron sites in the crystal structure of $\text{Nd}_2\text{Fe}_{14}\text{B}$, thus the observed spectrum must be decomposed into six individual subspectra, each with its own hyperfine field, quadrupole splitting, and isomer shift. The relative intensities of the six subspectra obey the 16:16:8:8:4:4 ratio corresponding to the multiplicities of the k_1 , k_2 , j_1 , j_2 , c , and e sites, respectively. The assignment of the six subspectra to the six iron sites is based on the near-neighbor environments of each iron site [37]. The selection of the sextet for the $8j_2$ site is quite straightforward. Since the $8j_2$ site has the largest number of iron near-neighbors, it should have the largest hyperfine field among the six iron sites. The subspectrum of the $8j_2$ site is clearly associated with the outermost line at positive velocity ($\sim 6\text{mm/s}$). The two strongest sites $16k_1$ and $16k_2$ must be related to the two well-split peaks at around -5mm/s . Both sites have the same number of iron near-neighbors, but the $16k_1$ site has one boron near-neighbor. Hence, we assigned the $16k_2$ site the sextet with the larger hyperfine field. The assignment of the $8j_1$ site is made on the basis of its relative area after the assignment of the $8j_2$ site. The two weakest sites, $4e$ and $4c$, have nine and eight iron near-neighbors, respectively, and therefore the sextet with the smaller hyperfine field is assigned to the $4c$ site. Starting values for the six subspectra parameters were taken from a number of published sources [21,37,56-58] and refined using a nonlinear least-squares fitting program. A total of 21 free parameters were used: baseline, linewidth, and total absorption plus isomer shift, quadrupole splitting, and hyperfine field for each of the six subspectra. The final parameters, summarized in Table 4.2, were found to reproduce the data most closely, and gave a χ^2 of 10.9 with a full width at half maximum of $0.296(2)\text{ mms}^{-1}$. The fit is shown in Fig. 4.2 as the solid

Table 4.2: Summary of isomer shift (δ), quadrupole splitting (Δ) and hyperfine field (B_{hf}) for the six iron sites in $\text{Nd}_2\text{Fe}_{14}\text{B}$ at room temperature. Isomer shifts are given relative to $\alpha - \text{Fe}$ at room temperature.

Site	Occupation	δ (mm/s)	Δ (mm/s)	B_{hf} (T)
		± 0.01	± 0.01	± 0.1
<i>e</i>	1	0.01	-0.78	28.8
<i>c</i>	1	-0.07	0.07	25.6
<i>j</i> ₁	2	-0.04	0.29	27.9
<i>j</i> ₂	2	0.10	0.65	34.3
<i>k</i> ₁	4	-0.01	0.26	28.8
<i>k</i> ₂	4	-0.09	0.17	30.6

line through the data points. The parameters are very close to those found by Long *et al* [37].

The Mössbauer spectrum of the source sample for $\text{Nd}_2\text{Fe}_{14}\text{B}$ is shown in Fig. 4.3. It was obtained using the conversion electron detector described in section 3.4. The spectrum has the typical low baseline counts ($\sim 80\text{k}$ in two weeks counting time) and high signal strength. It was fitted by taking the parameters obtained from the reference spectrum and allowing only the off-resonance baseline, linewidth, and the intensities of the individual subspectra to vary. The fit is shown in Fig 4.3 as the solid line through the data.

Before we try to analyze the Co site preferences by referring to the results of the computer fit, it is useful to compare visually the source spectrum with that of the reference. Fig. 4.4 displays both reference and source spectrum, where the source spectrum has been inverted in order to facilitate comparison with the reference spectrum. If the cobalt simply substituted randomly for iron in the structure then the source spectrum would look exactly the same as that of the reference sample. Clearly this is not the case as we can see from the Fig. 4.4 and we can conclude

Figure 4.3: Room temperature Mössbauer spectrum of the source for $\text{Nd}_2\text{Fe}_{14}\text{B}$. The spectrum is measured using the conversion electron detector. The solid line represents the fit to the data.

Figure 4.4: Mössbauer spectrum of the reference and source samples for $\text{Nd}_2\text{Fe}_{14}\text{B}$ at room temperature. The source spectrum has been inverted. Arrows indicate the position of the $8j_2$ peak at 6mm/s , absent from the source spectrum.

Figure 4.5: The deviation (%) of fitted Co site occupations from random occupation for the $\text{Nd}_2\text{Fe}_{14}\text{B}$ source.

that cobalt substitutes preferentially on certain sites. The most obvious difference is that the line at $+6\text{mms}^{-1}$ due to the j_2 site is missing from the source spectrum, indicating a strong Co avoidance of this site. However, a visual determination of Co site preferences for the other five sites is not so straightforward. The results of the computer fit are summarized in Fig. 4.5, which shows the percent deviations of Co occupations from a random distribution on the six crystallographically inequivalent iron sites. These results indicate clearly the preference of cobalt for the six sites in $\text{Nd}_2\text{Fe}_{14}\text{B}$. It confirms that the $8j_2$ site is strongly avoided by cobalt. It also shows that Co prefers the $8j_1$ and $16k_2$ sites and shows a small avoidance of the $4c$ site while populating the $16k_1$ and $4e$ essentially at random.

As we mentioned in the introduction of this thesis, a considerable amount of

data on Co site preferences in $\text{Nd}_2\text{Fe}_{14}\text{B}$ has been obtained using neutron diffraction [20], standard Mössbauer spectroscopy, [19,21,22,24-26] and NMR [17,32,59]. Substantial conflicting results, on site preference in this compound, were reported in these studies.

Neutron diffraction $\text{Nd}_2(\text{Fe}_{1-x}\text{Co}_x)_{14}\text{B}$ reveals a strong Co avoidance of the $8j_2$ site [11]. A weak Co preference for the $4e$ site becomes clear in the relatively high Co concentration alloys. It was concluded that Co occupies near-randomly on the $16k_1$, $16k_2$, $8j_1$, and $4c$ sites. The deviation of the fitted Co occupancies in these four sites from a random distribution did not show a trend throughout the series as seen for the $8j_2$ and $4e$ sites. However, it should be pointed out that the resulting Co occupancies from their calculated patterns actually give a systematic excess Co on the $8j_1$ in the alloys from $x = 0.1$ to $x = 0.5$. The amount of excess Co decreases from 70% to 8% with increasing Co contents. This normally should be a clear indication of Co preference for this site. Such deviation is also observed for the $16k_2$ site in the low Co concentration alloys. These results indicate the complications which could be caused at high Co concentration alloys for neutron diffraction studies and reflect the drawbacks of the indirect determination of the site preference.

Most of the studies on Co site preference in $\text{Nd}_2\text{Fe}_{14}\text{B}$ were carried out using conventional Mössbauer technique. Therefore, they are the major source of the conflicting results. As we summarized in the introduction, while most of these studies agree on the strong avoidance of Co for the $8j_2$ site, they also produced the results such as (i) Co favors the $16k_1$ and $16k_2$ while avoiding the $8j_1$ and $8j_2$ sites [25]; and (ii) no preferential Co substitution is observed at all [26,27]. One major factor which caused such diversity of the results is the poor resolved spectrum obtained for Co substituted alloys. With increasing Co concentrations, the small

features characterizing the difference in hyperfine fields at various iron sites are diminished and finally collapse into the just six broad lines when about 30% Fe is replaced by Co as we generally see in the spectra obtained from conventional Mössbauer studies. The reduction of hyperfine fields at Fe sites and the broad peaks can prevent from uniquely decomposing an observed spectrum into subspectra associated with the individual iron sites. As a result, the correctness of data analysis is called into question. It is worthwhile to emphasize, once again, the advantage of our Mössbauer technique in which the hyperfine parameters used for fitting the subspectra of the Co-doped sample are taken from the reference spectrum and only the intensities of the subspectra of the Co-doped sample are allowed to be adjustable. This unique feature enhances greatly the reliability of our data analysis.

Both ^{57}Fe and ^{59}Co NMR studies find a strong preference of Co to enter the $16k_2$ site [32,59]. The other results reported by Zhang *et al.* [17], such as Co avoidance of the $16k_1$ and $4e$ sites, are less evident since there is no simple relationship between signal strength and site occupancy. Moreover, they even fail to observe the Co avoidance of the $8j_2$ site, which is seen by both neutron diffraction and standard Mössbauer spectroscopy and is the clearest result obtained in this work. This indicates the limitation of NMR as a tool to study Co site preferences.

To summarize, our results give the most convincing evidence that Co avoids the $8j_2$ site. It is interesting to mention here the Mössbauer experiments made by van Noort *et al.* [21] on $\text{Nd}_2\text{Co}_{14}\text{B}$ doped with 2% ^{57}Fe -enriched iron. These experiments showed that Fe, in contrast to Co, has a strong preference for occupying the $8j_2$ site, in good agreement with the results obtained in this work. This preference, which is observed at all cobalt concentrations from $x = 10^{-6}$ to $x=0.98$ in $\text{Nd}_2(\text{Fe}_{1-x}\text{Co}_x)_{14}\text{B}$, implies that its origin is not controlled by the Co-Co and Fe-Fe exchange interactions.

We also find relatively strong preferences of Co for the $8j_1$ and $16k_2$ sites and a weak Co avoidance of the $4c$ site. We do not see any evidence either for selective Co substitution on the $4e$ site reported from neutron diffraction measurements [11] or for Co avoiding both $4e$ and $16k_1$ sites observed by NMR [17,32].

4.1.2 R_2Fe_{17} ($R = Nd, Gd, Dy$)

X-ray diffraction patterns shown in Fig. 4.6 confirmed that the alloys of Gd_2Fe_{17} and Dy_2Fe_{17} had the hexagonal Th_2Ni_{17} ($P6_3/mmc$) type structure and those of Nd_2Fe_{17} had the rhombohedral Th_2Zn_{17} ($R\bar{3}m$) type structure. Both x-ray and TGA measurements showed that all the samples were single phase except the source samples of Gd_2Fe_{17} and Dy_2Fe_{17} which contained a few percent of α -Fe. For the samples with hexagonal structure, no measurable line broadening was observed in either the x-ray or Mössbauer spectra, therefore we can conclude that no significant disorder exists in these alloys as reported by Givord *et al* [60]. The measured values of Curie temperatures for Nd_2Fe_{17} , Gd_2Fe_{17} , and Dy_2Fe_{17} are 343K, 486K, and 400K, respectively. The TGA curves for the reference samples of R_2Fe_{17} ($R = Nd, Gd, Dy$) are shown in Fig. 4.7.

Figure 4.8 shows the Mössbauer spectra for the reference samples of R_2Fe_{17} ($R = Nd, Gd, Dy$). The spectrum of Gd_2Fe_{17} was measured at room temperature, while the spectra of Nd_2Fe_{17} and Dy_2Fe_{17} were taken at liquid nitrogen temperature (77K) since their low T_c leads to insufficient resolution of the subspectra at room temperature. It is clear that the spectra of Nd_2Fe_{17} and Dy_2Fe_{17} are quite well resolved and individual subspectra may be distinguished.

Similar to the spectrum of $Nd_2Fe_{14}B$, the spectra of R_2Fe_{17} are also very complex because of their complex crystal structures. There are four crystallographically dis-

Figure 4.6: X-ray diffraction patterns for the reference samples of R_2Fe_{17} ($R = Nd, Gd, Dy$).

Figure 4.7: TGA curves for the reference samples of R_2Fe_{17} ($\text{R} = \text{Nd}, \text{Gd}, \text{Dy}$).

Figure 4.8: Reference Mössbauer spectra of R_2Fe_{17} ($\text{R} = \text{Nd}, \text{Gd}, \text{Dy}$). The spectrum of $\text{Gd}_2\text{Fe}_{17}$ was obtained at room temperature, and the spectra of $\text{Nd}_2\text{Fe}_{17}$ and $\text{Dy}_2\text{Fe}_{17}$ were at 77 K.

inct iron sites in both types of R_2Fe_{17} crystal structures. These sites are denoted by Wyckoff notations $6c(4f)$, $9d(6g)$, $18f(12j)$, and $18h(12k)$, where the site notations are given for the rhombohedral structure, with corresponding hexagonal notation in parentheses. To fit the spectrum of R_2Fe_{17} , we need at least four subspectra in the intensity ratio of 2:3:6:6 corresponding to the crystallographic multiplicities of the sites. Unlike $Nd_2Fe_{14}B$ where the magnetic easy direction is along the c -axis, the R_2Fe_{17} compounds have the easy direction of magnetization lying in the basal plane (either in the ab plane in the case of Gd_2Fe_{17} or along the a or b axes in Nd_2Fe_{17} and Dy_2Fe_{17} [30]). This further complicates the analysis of these spectra because it leads to the magnetic inequivalence of crystallographically equivalent sites as discussed in Section 2.3. A further magnetic subsplitting, therefore, must be included in the fitting. Previous Mössbauer studies on R_2Fe_{17} have shown that all iron sites, excluding the dumbbell site $6c(4f)$, should be split into several groups in order to take account of the existence of magnetically inequivalent sites [30,61,62].

In the present work, the spectrum of Nd_2Fe_{17} was fitted with six subspectra in the intensity ratio 2:3:2:4:2:4 corresponding to the occupations of the iron sites $c : d : f_1 : f_2 : h_1 : h_2$, where a 1:2 magnetic subsplitting of the $18f$ and $18h$ sites was included. The spectra of Gd_2Fe_{17} and Dy_2Fe_{17} were fitted with eight subspectra, including a 1:2 subsplitting for the $(6g)$ and $(12k)$ sites and a 1:1:1 ratio for the $(12j)$ site. Again, we have assigned the subspectra to the four iron sites by considering the near-neighbor environments of each iron site. The $6c(4f)$ site, with the most iron neighbors and the fewest rare-earth neighbors, should have the largest hyperfine field. It is also evident from the Fig. 4.8 that the outermost small peak at positive velocity in each spectrum is associated with the $6c(4f)$ site. As for the two equal intensity sites $18f(12j)$ and $18h(12k)$, the $18f(12j)$ site has a larger hyperfine field

than the $18h(12k)$ site since the former site has more iron near neighbors and fewer rare-earth neighbors. The $9d(6g)$ site can be distinguished by its intensity from the two strongest sites. The fits are shown as solid lines in Fig. 4.8. The final hyperfine parameters are given in Table 4.3. Also included in the table are the linewidths and χ^2 generated from the fits. The resulting average hyperfine fields for the four iron sites was found to decrease in the order $6c(4f) > 9d(6g) \sim 18f(12j) > 18h(12k)$. The parameters are in agreement with those found by previous work[30]. The assignments of hyperfine field is consistent also with neutron diffraction results on the $\text{Nd}_2\text{Fe}_{17}$ [18] and band structure calculation on Y_2Fe_{17} [63].

Figures 4.9, 4.10, and 4.11 show a comparison between the spectrum of the reference sample and that of the source sample for the three compounds. A common feature observed in these figures is the absence of the outermost line at positive velocity (indicated by the arrows) from all source spectra, indicating almost total Co avoidance of this site ($6c(4f)$). To further analyze the Co distribution among the four iron sites, the source spectra were fitted using the parameters from the reference spectra. The final fits are shown as solid lines in the Figs. 4.9–4.11. The results for Co site preferences obtained from the fits are demonstrated in Fig. 4.12. It is interesting to note that quite identical Co site preferences in the iron sites $6c(4f)$ and $9d(6g)$ are observed in both rhombohedral and hexagonal type R_2Fe_{17} structure. Cobalt, while it occupies preferentially the $9d(6g)$ site, avoids almost entirely the dumbbell site ($6c(4f)$). The Co preferences in the other two sites, however, exhibit a marked different picture in the two structures. In the rhombohedral $\text{Nd}_2\text{Fe}_{17}$, Co shows a clear preference for the $18f$ and $18h$ sites whereas in the two hexagonal samples it populates randomly in the $(12j)$ and $(12k)$ sites. The fact that similar results are obtained for $\text{Gd}_2\text{Fe}_{17}$ and $\text{Dy}_2\text{Fe}_{17}$ are consistent with the assumption

Table 4.3: Summary of fitted parameters (including χ^2 , full linewidth at half maximum (LW), isomer shift (δ), quadrupole splitting (Δ) and hyperfine field (B_{hf})) for the spectra of R_2Fe_{17} ($R = Nd, Gd, Dy$). The Mössbauer spectra of Nd_2Fe_{17} and Dy_2Fe_{17} were obtained at 77 K, while that of Gd_2Fe_{17} obtained at room temperature. Isomer shifts are given relative to $\alpha - Fe$ at room temperature.

compound	Site	Occupation	δ (mm/s)	Δ (mm/s)	B_{hf} (T)	χ^2	LW (mm/s)
Nd_2Fe_{17}	<i>h</i>	4	± 0.01	± 0.02	± 0.1	16.1	0.32
		2	0.06	-0.29	26.6		
	<i>f</i>	4	0.06	0.42	27.8		
		2	0.00	-0.07	31.0		
	<i>d</i>	2	0.00	0.58	27.2		
		3	-0.08	0.12	28.2		
	<i>c</i>	2	0.22	0.05	34.7		
Gd_2Fe_{17}	<i>k</i>	4	-0.15	-0.16	23.5	3.17	0.30
		2	-0.15	0.48	22.9		
	<i>j</i>	2	-0.09	-0.43	26.5		
		2	-0.09	0.07	26.7		
		2	-0.09	-0.04	21.2		
		2	-0.09	-0.04	21.2		
	<i>g</i>	2	-0.11	0.09	25.6		
		1	-0.11	0.30	23.9		
	<i>f</i>	2	0.06	0.05	30.2		
Dy_2Fe_{17}	<i>k</i>	4	0.02	0.16	31.1	6.8	0.32
		2	0.02	-0.26	26.3		
	<i>j</i>	2	0.05	0.42	26.8		
		2	0.05	0.25	27.0		
		2	0.05	-0.41	32.2		
		2	0.05	-0.41	32.2		
	<i>g</i>	2	-0.07	-0.03	30.6		
		1	-0.07	0.27	29.1		
	<i>f</i>	2	0.20	0.07	36.1

Figure 4.9: Mössbauer spectrum of the reference and source samples for $\text{Nd}_2\text{Fe}_{17}$ at 77K. The theoretical spectra are shown as solid lines in the figure. The source spectrum was inverted. Arrows indicate the line of the 6c site at $\sim 5.8\text{mm/s}$, absent from the source spectrum.

Figure 4.10: Mössbauer spectrum of the reference and source samples for Gd_2Fe_{17} at 295K. The fits to the data are shown as solid lines. Arrows indicate the line of 4f site at $\sim 4.7\text{mm/s}$, absent from the source spectrum.

Figure 4.11: Mössbauer spectrum of the reference and source samples for $\text{Dy}_2\text{Fe}_{17}$ at 77K. The fits to the data are shown as solid lines in the figure. The source spectrum was inverted. Arrows indicate the peak of the 4f site at $\sim 6.0\text{mm/s}$, absent from the source spectrum.

Figure 4.12: The deviation (%) of the fitted site intensities from random occupation for the Co doped samples of R_2Fe_{17} ($R = Nd, Gd, Dy$).

that the type of rare earth atoms, for the same structure, cannot affect significantly the Co site preferences on the iron sites.

There exists a number of neutron diffraction [18,28,29] and conventional Mössbauer spectroscopy [30,31,64,65] investigations of Co site preferences in both rhombohedral and hexagonal R_2Fe_{17} alloys. All conventional Mössbauer measurements show a definite tendency for Co to avoid the $6c(4f)$ site, but for the other three sites, no Co site preferences were reported by these authors. Although the three neutron diffraction measurements also observed the Co avoidance of the $6c(4f)$, they arrive at diametrically opposed conclusions on the other three sites. The earlier neutron diffraction work [28] on rhombohedral $Y_2(Fe, Co)_{17}$ finds a preference of Co for the $18f$ site, with random occupations for $9d$ and $18h$ sites, while the more recent study

[18] on $\text{Nd}_2(\text{Fe}, \text{Co})_{17}$ reveals preferred Co occupancy of $9d$ and $18h$ sites, with a slight deficiency on the $18f$ site. As mentioned above, the type of rare earth atoms cannot account for this contradiction, and the different conclusions reached by the two studies serve to emphasize the problems in using indirect methods to determine Co site preferences in these compounds.

There is unanimous agreement among the various studies conducted, irrespective of the techniques used, that Co shows a strong tendency to avoid the dumbbell site $6c(4f)$. This is not surprising if one considers the fact that the dumbbell site $6c(4f)$ in R_2Fe_{17} and the $8j_2$ site in $\text{Nd}_2\text{Fe}_{14}\text{B}$ are cognate magnetically as well as crystallographically [11]. The results obtained in this work also show that in the rhombohedral $\text{Nd}_2\text{Fe}_{17}$, Co tends to avoid the $18f$ site while preferentially occupying the $18h$ and $9d$ sites. These results agree very well with that obtained by neutron diffraction [18] in the same compound except for the $18f$ site where almost random occupation of Co atoms was previously observed. For the two hexagonal $\text{Gd}_2\text{Fe}_{17}$ and $\text{Dy}_2\text{Fe}_{17}$, our results produce a consistent site preference of Co for the $6g$ site while occupying the remaining two sites $12j$ and $12k$ at random. The slight differences between Co site preferences in the rhombohedral and hexagonal compounds reflect their differences in the local atomic environments. This suggests that the local atomic environments may play a controlling role in the Co site preferences.

4.1.3 $\text{Er}_6\text{Fe}_{23}$

Both reference and source samples of $\text{Er}_6\text{Fe}_{23}$ are found to be single phase with the face-centered cubic $\text{Th}_6\text{Mn}_{23}$ structure ($Fm\bar{3}m$). The Curie temperature of both samples is 493 K. The x-ray diffraction pattern and TGA curve for the reference sample are shown in Fig. 4.13.

The room temperature Mössbauer spectrum of the reference, shown in Fig. 4.14, was fitted with four subspectra in the ratio 1:6:8:8 corresponding to the iron occupations of the $4b$, $24d$, $32f_1$ and $32f_2$ sites, respectively. A further 6:2 magnetic subsplitting was included for the f_1 and f_2 sites and a 4:2 for the d site as the magnetic easy direction is along the $[111]$ direction [30]. At least one site can be easily identified from the spectrum. That is the site $4b$, which has the least Fe populations and must be associated with the smallest peaks in the spectrum. However, the assignments of the parameters of the subspectra to the rest of iron sites is not so straightforward, especially for the two sites with equal intensities (f_1 and f_2). According to the results from both neutron diffraction and band structure calculations on Y_6Fe_{23} , [62,65] the iron magnetic moment at the f_2 site is much greater than that at the f_1 site. Therefore we have assigned the larger hyperfine field sextet to the f_2 site and the smaller one to the f_1 . This assignment is also consistent with the argument that the hyperfine field on each site is predominately determined by its number of iron near-neighbors as the f_2 site has one more iron atom in its near-neighbors than the f_1 [38]. The solid line in Fig. 4.14 represents the fit to the data. Fitted parameters are listed in Table 4.4.

Figure 4.15 shows a comparison between the spectrum of the reference sample and that obtained from the ^{57}Co -doped source sample. It is clear from a visual inspection of the source spectrum that the line at 4.2mm s^{-1} (indicated by an

Figure 4.13: (a) X-ray diffraction pattern and (b) TGA curve for the reference sample of $\text{Er}_6\text{Fe}_{23}$.

Figure 4.14: Room temperature Mössbauer spectrum of the reference sample for $\text{Er}_6\text{Fe}_{23}$. The solid line in the figure represents the fit to the data.

Figure 4.15: Room temperature Mössbauer spectrum of the reference and source samples for $\text{Er}_6\text{Fe}_{23}$. The solid lines represent the fits to the data. Arrows indicate that the intensity of the f_2 peak at ~ 4.2 mm/s is greatly reduced in the source spectrum.

Table 4.4: Summary of isomer shift (δ), quadrupole splitting (Δ) and hyperfine field (B_{hf}) for the four iron sites in $\text{Er}_6\text{Fe}_{23}$ at room temperature. Isomer shifts are given relative to α -Fe at room temperature.

Site	Occupation	δ (mm/s)	Δ (mm/s)	B_{hf} (T)
		± 0.01	± 0.02	± 0.1
f_1	6	-0.16	-0.04	21.6
	2	-0.16	0.13	20.8
f_2	6	0.01	0.13	26.6
	2	0.01	-0.34	26.5
d	4	-0.14	0.03	23.8
	2	-0.14	0.00	22.9
b	1	-0.03	0.03	30.8

arrow) is greatly reduced in intensity and therefore Co tends to avoid this site (f_2). The observed cobalt occupations of the four crystallographically inequivalent iron sites are compared to values expected from a random distribution in Fig. 4.16. It is clear that Co favors the f_1 site and avoids the f_2 and b sites while occupying the d site essentially at random. No previous work has been done on cobalt site preferences in R_6Fe_{23} , however, a similar behaviour of Mn atoms was obtained in the $\text{Y}_6(\text{Fe}_{1-x}\text{Mn}_x)_{23}$ system using neutron diffraction [67]. In this system the Mn atoms prefer to occupy the f_2 site and Fe atoms the f_1 site.

Figure 4.16: The deviation (%) of the fitted Co site occupation from a random occupation for the Co doped $\text{Er}_6\text{Fe}_{23}$ sample.

4.1.4 DyFe₃

Both reference and cobalt doped samples were confirmed to have the rhombohedral PuNi₃ ($R\bar{3}m$) structure by x-ray diffraction. No presence of secondary phases was found in both samples. Figure 4.17 shows x-ray diffraction pattern and TGA curve for the reference samples of DyFe₃. TGA measurements found the Curie temperature to be 616 K for both samples. The compensation temperature ($M=0$) at 530 K can be seen in Fig. 4.17b.

Figure 4.18 is the Mössbauer spectrum of the reference sample. It was fitted with three subspectra in the ratio 1:2:6 corresponding to the occupations of the 3b, 6c, and 18h sites, respectively. Since the easy direction of the magnetization lies in the basal plane [66,67], we have included a further 2:2:2 magnetic subsplitting of the 18h site contributions. Kraan *et al.*[67] have concluded from the results of their fitted Mössbauer spectrum that the magnetization lies along the b-axis at 295 K, but in the basal plane when the temperature is lowered. In this instance the h site should split into two subgroups in the ratio of 2:4 at 295 K and hence the spectrum should be fitted with four subspectra in the ratio of 1:2:2:4. An attempt to fit this spectrum based on this idea, i.e. implying b axis magnetization, was unsuccessful. In particular, the fit was unable to reproduce the fine structure appearing on the outermost line at the positive velocity of the spectrum. We believe, therefore, the easy direction of magnetization lies in the the *ab* plane. The final fit to the spectrum is shown as solid line the Fig. 4.18. The parameters of the complete fit are given in Table 4.5. We have found the c site has the largest hyperfine field which agrees very well with previous Mössbauer results on DyFe₃ [67] and is also consistent with band structure calculations on YFe₃[62]. The source spectrum of DyFe₃ is shown in Fig. 4.19 together with that of the reference. Unlike previous samples, direct

Figure 4.17: (a) X-ray diffraction pattern and (b) TGA curve for the reference sample of DyFe_3 .

Figure 4.18: Room temperature Mössbauer spectrum of the reference sample for DyFe_3 . The solid line represents the theoretical fit.

Figure 4.19: Mössbauer spectrum of the reference and source samples for DyFe_3 at 295K. The fits are represented by the solid line through the data points.

Table 4.5: Summary of isomer shift (δ), quadrupole splitting (Δ) and hyperfine field (B_{hf}) for the three iron sites in DyFe_3 at room temperature. Isomer shifts are given relative to $\alpha - \text{Fe}$ at room temperature.

Site	Occupation	δ (mm/s)	Δ (mm/s)	B_{hf} (T)
		± 0.02	± 0.02	± 0.1
<i>h</i>	2	-0.14	0.33	21.6
	2	-0.14	-0.444	20.9
	2	-0.14	0.06	21.4
<i>c</i>	2	-0.11	0.46	22.5
<i>b</i>	1	-0.07	0.40	21.4

information about cobalt site preferences in DyFe_3 can not be obtained from a visual inspection of the source spectrum. However a complete computer fit of the source spectrum reveals that cobalt preferentially occupies the 3*b* site and avoids the 6*c* site as shown in Fig. 4.20. Previous Mössbauer study on $\text{R}(\text{Fe}_{1-x}\text{Co}_x)_3$, ($\text{R} = \text{Dy, Y}$), by Arif *et al.*[68] showed no preferential occupancies in these systems, but the results of a more recent neutron diffraction work on $\text{Er}(\text{Fe}_{1-x}\text{Co}_x)_3$ [69] are in very good agreement with our results.

Figure 4.20: The deviation (%) of fitted Co site occupations from a random distribution for source sample of DyFe₃.

4.1.5 ThFe₅

Figure 4.21 are TGA curves for both the as-made and annealed reference samples of ThFe₅. As can be seen from Fig. 4.21a, the as-made samples contain mainly the Th₂Fe₁₇, ThFe₃, and Th₂Fe₇ phases with the presence of only a small fraction of ThFe₅ phase. However, the annealed sample of ThFe₅ comprises the majority of the ThFe₅ while only small amount of the Th₂Fe₁₇ phase is still present. Both x-ray diffraction and TGA measurements showed that the reference and source samples had mainly the ThFe₅ phase with the hexagonal CaCu₅ structure (*P6/mmm*). Both samples were found to contain some amounts of Th₂Fe₁₇ phase. The measured values of the Curie temperatures for ThFe₅ and Th₂Fe₁₇ are 685K and 302 K, respectively.

The Mössbauer spectrum of the reference sample measured at room temperature is shown in Fig. 4.22a. The extra lines at the center of the spectrum are apparently due to the secondary phase, Th₂Fe₁₇ whose Mössbauer spectrum is shown in Fig. 4.22b. Fortunately, the T_c of Th₂Fe₁₇ is near room temperature and much lower than that of ThFe₅. Therefore it allows us to distinguish the contributions of these two phases in the Mössbauer spectrum. More importantly, the lines 1 and 6 of ThFe₅ in the spectrum are distinct, and thus the subspectra corresponding to the two crystallographically inequivalent iron sites may be distinguished unambiguously.

The spectrum is fitted with two subspectra in the ratio 3:2 corresponding to the occupations of *g* and *c* sites of the ThFe₅ phase and four subspectra associated with the four iron sites of Th₂Fe₁₇ which accounts for ~ 25% of the total intensities. Starting values of the hyperfine parameters were taken from the literature [30,72]. As usual, a further 1:1:1 magnetic subsplitting of the *g* site was included to take account of the magnetization being in the basal plane. Fitted parameters of ThFe₅ are given in Table 4.6. The results are consistent with those obtained by Gubbens

Figure 4.21: TGA curves for both the as-made and annealed reference samples of ThFe₅. The multi-phase nature of the as-made sample is clearly seen from the TGA curve shown in (b).

Figure 4.22: Room temperature Mössbauer spectrum for the reference of ThFe₅. The theoretical spectrum, shown as solid line, include the subspectra of the Th₂Fe₁₇ phase.

Table 4.6: Summary of isomer shift (δ), quadrupole splitting (Δ) and hyperfine field (B_{hf}) for the two iron sites in ThFe_5 at room temperature. Isomer shifts are given relative to $\alpha\text{-Fe}$ at room temperature.

Site	Occupation	δ (mm/s)	Δ (mm/s)	B_{hf} (T)
		± 0.02	± 0.02	± 0.1
c	2	-0.10	0.48	19.7
g	1	-0.08	-0.40	21.6
	1	-0.08	-0.08	24.4
	1	-0.08	0.40	22.2

et al. [30,70]

The source spectrum is compared with that of reference in Fig. 4.23. For the sake of comparing the source spectrum with the reference spectrum, the contributions of the $\text{Th}_2\text{Fe}_{17}$ phase ($\sim 40\%$) to the signal strength were subtracted from the source spectrum and that of $\sim 25\%$ were also subtracted from the reference spectrum. The scatter in source spectrum is clearly due to the subtraction of $\text{Th}_2\text{Fe}_{17}$ contributions. It is quite clear that the intensity of the outermost lines in the source spectrum are reduced, indicating cobalt avoidance of this site (3g). The results of the fitted source spectrum, summarized in Fig. 4.24, clearly confirm that Co, indeed, prefers the c site over the g site in the ThFe_5 compound. These results agree very well with that obtained by the neutron diffraction studies on the $\text{Th}(\text{Fe}_{1-x}\text{Co}_x)_5$ alloys[15,16].

Figure 4.23: Room temperature Mössbauer spectra of the reference and source samples for ThFe_5 . The contributions of impurity phase $\text{Th}_2\text{Fe}_{17}$ to the signal were subtracted from both spectra. The fits to the spectra are shown as solid line through the data points.

Figure 4.24: The deviation (%) of fitted Co site occupations from a random distribution for source sample of ThFe₅.

4.2 Discussion

The results of Co site preferences obtained in this work are summarized in Table 4.7. The table lists the observed Co occupations, the Co site preference, which is represented by the ratio of observed Co occupation to random occupation, that is if the ratio is greater than one, Co prefers the site; otherwise, it avoids the site. The table also includes the hyperfine fields (B_{hf}) or average hyperfine fields in the case of magnetic subsplittings for some sites. The clearest results obtained here are the strong Co avoidances of the $8j_2$ site in $Nd_2Fe_{14}B$, $6c(4f)$ sites in R_2Fe_{17} ($R = Nd, Gd, Dy$), and $4b$ and $32f_2$ sites in Er_6Fe_{23} . The results also show that Co strongly prefers the sites $8j_1$ and $16k_2$ in $Nd_2Fe_{14}B$, $9d$ and $18h$ in Nd_2Fe_{17} , $(6g)$ in both Gd_2Fe_{17} and Dy_2Fe_{17} , $2c$ in $ThFe_5$, $32f_1$ in Er_6Fe_{23} , and $3b$ in $DyFe_3$. It is quite remarkable that cobalt should exhibit such strong site preferences in these iron-based rare earth intermetallic compounds. Considering that Co and Fe have a very similar chemistry and a close atomic size and that all these Fe-based compounds studied in this work can also be formed with Co, one would believe naturally that Co should substitute randomly for Fe in these compounds. It is interesting to note from an inspection of Table 4.7 that all of the sites with the largest hyperfine fields are strongly avoided by cobalt. In Fig. 4.25, we have plotted the Co site preference against the hyperfine field of the sites for each compound. It follows from Fig. 4.25 that cobalt, indeed, favors generally the sites with the smaller hyperfine fields, while avoiding the sites with relative large hyperfine fields. It is very fortunate from the technological point of view that cobalt substitutes for iron in such manner, reducing the loss of magnetization associated with adding a low moment transition metal.

The question arises as to the origins of these cobalt site preferences. The most

Table 4.7: Summary of observed Co occupations and the site preferences as derived from the ratio of observed to random occupation in various Fe-R compounds. The hyperfine field B_{hf} (or average hyperfine field in the case of magnetic subsplitting used in the fitting) is also included in the table. The hyperfine parameters are corresponding to the room temperature values except for Nd_2Fe_{17} and Dy_2Fe_{17} for which they were obtained at 77 K.

Compound	Atomic site	Cobalt occupations		Site preference	B_{hf} (T)
		random	observed		
$Nd_2Fe_{14}B$	4e	7.14	7.54	1.06	28.8
	4c	7.14	6.36	0.89	25.6
	8j ₁	14.3	19.9	1.39	27.9
	8j ₂	14.3	2.95	0.21	34.3
	16k ₁	28.6	27.2	0.95	28.8
	16k ₂	28.6	36.1	1.26	30.6
Nd_2Fe_{17}	6c	11.8	3.01	0.26	34.7
	9d	17.6	24.3	1.37	28.2
	18f	35.3	27.1	0.77	29.7
	18h	35.3	45.6	1.29	27.2
Gd_2Fe_{17}	4f	11.8	2.35	0.20	30.2
	6g	17.6	25.7	1.46	25.0
	12j	35.3	36.4	1.03	24.8
	12k	35.3	35.5	1.01	23.3
Dy_2Fe_{17}	4f	11.8	2.0	0.17	36.1
	6g	17.6	25.2	1.43	29.9
	12j	35.3	36.7	1.04	29.5
	12k	35.3	36.1	1.03	28.7
$ThFe_5$	2c	40.0	55.5	1.38	19.7
	3g	60.0	44.5	0.74	22.7
Er_6Fe_{23}	4b	4.35	0.90	0.21	30.5
	24d	26.1	29.6	1.13	23.5
	32f ₁	34.8	50.0	1.44	21.4
	32f ₂	34.8	19.5	0.56	26.6
$DyFe_3$	3b	11.1	15.6	1.41	21.4
	6c	22.2	17.3	0.78	22.5
	18h	66.7	67.1	1.01	21.3

Figure 4.25: Plots of site preference vs hyperfine field (B_{hf}) for the iron-based rare earth compounds studied in this work.

probable factors which could lead to these site preferences are the site volume and other parameters of the local atomic environment of each site, for example, the type and number of nearest-neighbors. One measure of a local atomic environment is the Wigner-Seitz cell [73] associated with the atomic site. Such cell provides a well-defined method to determine the nearest-neighbor environment for a site. The cells yield an indication of site symmetry and volume as well as number and type of nearest neighbors. Hence the Wigner-Seitz cell analysis is applied here to obtain the local atomic environment of various sites in all the compounds investigated in this work. For the cell calculations, the crystallographic data for each compound, given in Table 4.1, are used. We have assumed that all atoms are spherical and the atomic size is independent on the number and type of nearest-neighbors. This approximation may not be strictly true as the atomic coordination may have some effect on atomic sizes as suggested by Pearson [74]. The atomic radii of the elements are taken to be 1.26Å(Fe), 1.82(Nd), 1.79(Gd), 1.80(Dy), 1.78(Er), 1.80(Th), and 0.98(B), respectively. The resulting nearest-neighbor environment and site volume for each site of the compounds are summarized in Table 4.8. More detailed results of this analysis are tabulated in Appendix A. We have examined the Wigner-Seitz (i.e. Voronoi) polyhedra for all of the transition-metal sites and found that they are essentially regular. In other words, the cell volume obtained from such an analysis can accommodate an almost spherical atom. Some examples of the polyhedra for the transition-metal sites in compounds $\text{Nd}_2\text{Fe}_{14}\text{B}$ and $\text{Nd}_2\text{Fe}_{17}$ are shown in Figure 4.26.

It appears by examining Tables 4.7 and 4.8 that the Fe coordination of the sites may play a role in Co site preferences. The site with the highest number of iron neighbors in each compound is generally avoided by cobalt atoms. In Fig. 4.27 we have plotted the Co site preference verse the fraction of nearest-neighbor Fe atoms

Table 4.8: Summary of site volume and number of nearest neighbors (number of Fe nearest-neighbors n_{Fe} and number of rare-earth nearest-neighbors n_R) for transition-metal sites in Fe-based compounds as determined from Wigner-Seitz analysis.

<i>Compound</i>	<i>Atomic site</i>	<i>Site volume ($\text{\AA}^3$)</i>	n_{Fe}	n_R
Nd ₂ Fe ₁₄ B	4e	11.76	9	2
	4c	12.18	8	4
	8j ₁	12.24	9	3
	8j ₂	12.73	12	2
	16k ₁	11.71	10	2
	16k ₂	11.51	10	2
Nd ₂ Fe ₁₇	6c	12.24	13	1
	9d	11.17	10	2
	18f	11.73	11	2
	18h	12.22	9	3
Gd ₂ Fe ₁₇	4f	12.64	13	1
	6g	11.14	10	2
	12j	11.81	11	2
	12k	11.89	9	3
Dy ₂ Fe ₁₇	4f	12.40	13	1
	6g	10.92	10	2
	12j	11.55	11	2
	12k	11.63	9	3
ThFe ₅	2c	11.34	9	3
	3g	12.00	8	4
Er ₆ Fe ₂₃	4b	13.11	8	6
	24d	11.36	8	4
	32f ₁	10.88	9	3
	32f ₂	11.98	10	3
DyFe ₃	3b	10.90	6	6
	6c	11.66	9	3
	18h	11.45	7	5

Figure 4.26: Wigner-Seitz (i.e. Voronoi) polyhedra for the iron sites $8j_1$ and $8j_2$ in $\text{Nd}_2\text{Fe}_{14}\text{B}$ and $18h$ and $6c$ in $\text{Nd}_2\text{Fe}_{17}$.

for each transition site. Besides the strong Co avoidance of the sites with the highest Fe coordination, however, we have not seen any evidence of systematic dependence of the Co site preference on the number of Fe nearest-neighbors. The effects of the Fe-Fe interatomic distances on the Co site preferences have also been examined. We found no correlation between the shortest Fe-Fe distance for each site and the Co preference for the same site. Fig. 4.28 shows that there is some tendency for cobalt to prefer sites with short average Fe-Fe distances, however, the scatter is quite large and the trend most probably reflects the correlation between average bond length and site volume. The latter parameter is shown below to give a far better description on Co site preferences.

The site volume has been considered as one of the most important factors controlling the site preference by previous studies [8,21]. In the Mn substituted $\text{Er}_2\text{Fe}_{14}\text{B}$, for example, Fuerst *et al.* [8] find that the manganese affinity increases with increasing site volume for five of the six transition-metal sites. In studies on cobalt site preferences, however, the volume consideration has often led to controversy. The reason has been the lack of systematic and reliable data on Co site preferences. As demonstrated in this thesis, the systematic, reliable and exhaustive data collected in this work should allow a critical evaluation of the role of the site volume on Co site preferences. Figure 4.29 shows the observed Co site preference plotted against the site volume for all of the compounds studied in this work. It is remarkable that Co site preference exhibits such clear dependence on the site volume. As can be seen from Fig. 4.29, Co site preferences depend linearly on the site volume up to the value of $\sim 12.2\text{\AA}^3$, i.e. the Co affinity decreases with increasing site volume at a rate of $\sim 0.9\text{\AA}^{-3}$. A total Co avoidance is found for sites with volumes greater than $12.2\text{\AA}^3$ with the exception of two sites where Co actually shows a strong preference.

Figure 4.27: Plots of site preference vs fraction of Fe neighbors in the coordination for the iron-based rare earth compounds studied in this work.

Figure 4.28: Site preference (ratio of observed to random occupation) *vs* the average Fe-Fe interatomic distance of nearest neighbors for the iron-based rare earth compounds studied.

Figure 4.29: Site preference (ratio of observed to random occupation) vs site volume for the iron-based rare earth compounds studied in this work.

It is interesting to mention that the site volume for which Co shows a random occupation has a value of $\sim 11.6\text{\AA}^3$, as derived from the straight line fitted to the data points with volumes $< 12.2\text{\AA}^3$ in Fig 4.29. This value is found to be close to the volume occupied by iron in a closed-packed bcc lattice. In general, the sites with volume smaller than $\sim 11.6\text{\AA}^3$ is preferred by Co. It is clear that the Co atoms prefer sites with relatively small volume in these Fe based rare-earth compounds. We conclude here that the site volume plays the dominant role in controlling the selective substitution of Co for Fe in iron-based intermetallic compounds.

The behavior of Co substitution among the sites with volumes $\geq 12.2\text{\AA}^3$, however, remains to be explained. As can be seen from the Fig. 4.29, Co strongly prefers

two sites while it avoids completely the other five sites. Such extremely different behavior suggests that besides the site volume effect, there may be other factors controlling Co site preferences in these iron-based rare-earth compounds. The two Co preferred sites are the $8j_1$ site in $\text{Nd}_2\text{Fe}_{14}\text{B}$ and the $18h$ site in $\text{Nd}_2\text{Fe}_{17}$. From the Wigner-Seitz analysis, the sites $8j_1$ and $18h$ are found to have identical local atomic environments. Each site has 12 nearest-neighbors, of which three are neodymium atoms. The number of rare-earth nearest-neighbors in the two sites is substantially larger than that of the other sites in the crystal structures of these two compounds. On the other hand, the five sites, strongly avoided by Co, have generally the largest number of Fe nearest neighbors, while there are few rare earth nearest neighbors. It is quite possible that with site volume being substantially large, the Co substitutions among these sites are not controlled solely by the site volume but by a combination of the size effects and the affinity between various atoms. van Noort *et al.* [21] have made an estimate of relative bond strength among the cobalt, neodymium, and iron atoms from the corresponding heats of solution. They find that for Co the enthalpy of mixing with rare earth is negative and large (-62kJmole^{-1} for cobalt in neodymium), while for Fe that value is positive (2kJmole^{-1} for Fe in neodymium). According to enthalpy considerations, the atoms try to have mutual contact as much as possible when the enthalpy of mixing is negative. It follows, therefore, that Co atoms are expected to strongly prefer the $8j_1$ site in $\text{Nd}_2\text{Fe}_{14}\text{B}$ and the $18h$ site in $\text{Nd}_2\text{Fe}_{17}$, as is experimentally observed, while Fe atoms try to avoid them. It is also quite natural, based on enthalpy considerations, for cobalt not to compete with iron for occupying the other five sites since there are few rare earth nearest neighbors around these sites. More importantly, the large site volume of these sites is clearly attractive to iron atoms. Therefore, we believe that the enthalpy effects become

increasingly significant in controlling the Co substitutions in Fe-R compounds as the site volume becomes sufficiently large that both Co and Fe atoms can be easily accommodated.

In summary, we have demonstrated that the Co site preference is strongly controlled by the local atomic environment based on the analysis of Wigner-Seitz cell. The site volume is the dominant factor controlling the preferential substitution of Co at the iron sites with volume $< 12.2\text{\AA}^3$. The preferential occupations of Co decreases at a rate of $\sim 0.9\text{\AA}^{-3}$ with site volume. Co prefers the sites with relatively small volume in these Fe-based compounds. For site volumes $\geq 12.2\text{\AA}^3$, Co shows a total avoidance of these sites with the exception of two sites. It is found that as the site volume becomes sufficiently large, the negative enthalpy of mixing between Co and R plays an important role in the Co site preference in combination with the site volume effect and sites with more rare-earth nearest-neighbors are preferential occupied by Co. We have realized that there is much more theoretical work to be done in order to achieve a complete understanding of the fundamental mechanisms in controlling the site preference.

Chapter 5

Conclusions

We have performed a systematic study of cobalt site preferences in iron-based rare-earth intermetallic compounds using the Mössbauer source technique. It has been shown that the Mössbauer source technique offers a direct and unambiguous way to quantitatively determine cobalt site preferences in these iron-based compounds at extremely low Co doping levels ($\sim 1\text{ppm}$). The use of low Co content alloys allows cobalt to choose preferentially the various sites in the crystal structures without being influenced by unit cell volume changes and effects of Co-Co interactions. Therefore, the results obtained in this work reflect the true mechanisms controlling the preferential cobalt substitutions at the transition-metal sites in these compounds.

For our Mössbauer source measurements, we have constructed a resonant conversion electron detector utilising 90% ^{57}Fe enriched stainless steel foil. The importance of this detector is two fold: (i) the lightweight detector ($\sim 25\text{g}$) allows Mössbauer source measurements to be made at low temperatures by moving the detector and placing the source/sample in a cryostat; (ii) its high signal-to-noise ratio, which is a more than six-fold enhancement over standard transmission method with a proportional counter and an absorber, improves data quality as well as counting efficiency for the source samples.

Our results have given the most convincing evidence that cobalt substitutes preferentially in the iron-based rare-earth compounds. The clearest results are the strong Co avoidances of the $8j_2$ site in $\text{Nd}_2\text{Fe}_{14}\text{B}$, $6c(4f)$ sites in R_2Fe_{17} ($\text{R} = \text{Nd}, \text{Gd}, \text{Dy}$), and $4b$ and $32f_2$ sites in $\text{Er}_6\text{Fe}_{23}$. All these sites are found to be associated with the largest hyperfine field in each compound. The results also show that Co strongly prefers the sites $8j_1$ and $16k_2$ in $\text{Nd}_2\text{Fe}_{14}\text{B}$, $9d$ and $18h$ in $\text{Nd}_2\text{Fe}_{17}$, $(6g)$ in both $\text{Gd}_2\text{Fe}_{17}$ and $\text{Dy}_2\text{Fe}_{17}$, $2c$ in ThFe_5 , $32f_1$ in $\text{Er}_6\text{Fe}_{23}$, and $3b$ in DyFe_3 .

We have shown that cobalt site preferences in iron-based rare-earth compounds are strongly controlled by the local atomic environment based on the analysis of Wigner-Seitz cell. The site volume is the dominant factor controlling the preferential cobalt substitutions at the iron sites with volume $< 12.2\text{\AA}^3$. The cobalt preference for the sites is found to decrease linearly at a rate of $\sim 0.9\text{\AA}^{-3}$ with increasing site volume. In general, cobalt shows a preference for the sites with volume $< 11.8\text{\AA}^3$. As site volume becomes sufficiently large ($\geq 12.2\text{\AA}^3$), the negative enthalpy of mixing between Co and R plays a significant role in controlling the cobalt site preferences in combination with the site volume effects. The results show that cobalt avoids strongly the sites with relatively few R nearest-neighbors while preferring the sites with more R nearest-neighbors.

Appendix A

The programme (BLOKJE) for computing the Wigner-Seitze cell is provided by Prof. G. J. Long, University of Missouri-Rolla. It was written by L. Gelato, Université de Geneve, Switzerland [71].

The information read by programme includes: space group, lattice constants, coordinates in units of lattice constants, and the atomic radii. The crystallographic data used in these calculations are summarized in Table 4.1 for all of the compounds studied in this work. The following tables list interatomic distances, number and type of nearest-neighbors for each transition-metal site.

TABLE I. Interatomic distances (Å) of the nearest-neighbors in Nd₂Fe₁₄B

<i>Atom</i>	<i>Neighbors and distances</i>		<i>Atom</i>	<i>Neighbors and distances</i>	
Fe(4e)	2 B(g)	2.124	Fe(k ₁)	1 B(g)	2.096
	4 Fe(k ₁)	2.513		1 Fe(k ₂)	2.451
	2 Fe(j ₁)	2.533		1 Fe(e)	2.513
	1 Fe(e)	2.782		1 Fe(k ₂)	2.521
	2 Fe(j ₂)	2.789		1 Fe(k ₂)	2.526
	2 Nd(f)	3.205		1 Fe(c)	2.569
Fe(4c)	4 Fe(k ₂)	2.497		1 Fe(j ₁)	2.609
	4 Fe(k ₁)	2.569		1 Fe(k ₁)	2.613
	2 Nd(f)	3.119		1 Fe(j ₂)	2.714
	2 Nd(g)	3.399		1 Fe(j ₂)	2.763
Fe(j ₁)	2 Fe(k ₂)	2.392		1 Nd(f)	3.079
	1 Fe(j ₁)	2.439		1 Nd(g)	3.096
	1 Fe(e)	2.533		1 Fe(k ₁)	3.099
	2 Fe(k ₁)	2.609	Fe(k ₂)	1 Fe(j ₁)	2.392
	2 Fe(j ₂)	2.655		1 Fe(k ₁)	2.451
	1 Fe(j ₂)	2.773		1 Fe(c)	2.497
	1 Nd(f)	3.267		1 Fe(k ₁)	2.521
	2 Nd(g)	3.274		1 Fe(k ₁)	2.526
Fe(8j ₂)	2 Fe(k ₂)	2.635		1 Fe(k ₂)	2.548
	2 Fe(j ₁)	2.655		2 Fe(k ₂)	2.551
	2 Fe(k ₂)	2.661		1 Fe(j ₂)	2.635
	2 Fe(k ₁)	2.714		1 Fe(j ₂)	2.661
	2 Fe(k ₁)	2.763		1 Nd(f)	3.066
	1 Fe(e)	2.789		1 Nd(g)	3.284
	1 Nd(f)	3.063		1 Fe(j ₁)	2.773
	1 Nd(g)	3.145			

TABLE II. Interatomic distances ($\text{\AA}$) of the nearest-neighbors in rhombohedral $\text{Nd}_2\text{Fe}_{17}$.

<i>Atom</i>	<i>Neighbors and distances</i>		<i>Atom</i>	<i>Neighbors and distances</i>	
Fe(6c)	1 Fe(c)	2.393	Fe(18f)	2 Fe(d)	2.438
	3 Fe(d)	2.628		2 Fe(f)	2.453
	3 Fe(h)	2.715		2 Fe(h)	2.602
	6 Fe(f)	2.729		2 Fe(h)	2.638
	1 Nd(c)	2.957		2 Fe(c)	2.729
				2 Nd(c)	3.082
Fe(9d)	4 Fe(f)	2.438		1 Fe(f)	3.671
	4 Fe(h)	2.487	Fe(18h)	2 Fe(d)	2.487
	2 Fe(c)	2.628		2 Fe(h)	2.520
	2 Nd(c)	3.232		2 Fe(f)	2.602
				2 Fe(f)	2.639
				1 Fe(c)	2.715
				2 Nd(c)	3.088
				1 Nd(c)	3.386

TABLE III. Interatomic distances ($\text{\AA}$) of the nearest-neighbors in hexagonal $\text{Gd}_2\text{Fe}_{17}$.

<i>Atom</i>	<i>Neighbors and distances</i>		<i>Atom</i>	<i>Neighbors and distances</i>	
Fe(4f)	1 Fe(f)	2.420	Fe(18j)	2 Fe(g)	2.462
	3 Fe(g)	2.604		1 Fe(j)	2.566
	3 Fe(k)	2.652		2 Fe(k)	2.569
	6 Fe(j)	2.841		1 Fe(j)	2.574
	1 Gd(d)	2.962		2 Fe(k)	2.578
Fe(6g)	2 Fe(k)	2.453		1 Gd(d)	2.970
	2 Fe(k)	2.461		1 Gd(b)	2.970
	4 Fe(j)	2.462		2 Fe(f)	2.841
	2 Fe(f)	2.604		1 Fe(j)	3.356
	2 Gd(d)	3.218	Fe(18k)	1 Fe(g)	2.453
				1 Fe(g)	2.461
				2 Fe(k)	2.463
				1 Fe(j)	2.565
				1 Fe(j)	2.568
				1 Fe(j)	2.578
				1 Fe(j)	2.584
				1 Fe(f)	2.652
				1 Gd(b)	3.138
				1 Gd(d)	3.144
				1 Gd(b)	3.301

TABLE IV. Interatomic distances ($\text{\AA}$) of the nearest-neighbors in hexagonal $\text{Dy}_2\text{Fe}_{17}$.

<i>Atom</i>	<i>Neighbors and distances</i>		<i>Atom</i>	<i>Neighbors and distances</i>	
Fe(4 <i>f</i>)	1 Fe(<i>f</i>)	2.406	Fe(18 <i>j</i>)	2 Fe(<i>g</i>)	2.447
	3 Fe(<i>g</i>)	2.589		1 Fe(<i>j</i>)	2.551
	3 Fe(<i>k</i>)	2.636		2 Fe(<i>k</i>)	2.553
	6 Fe(<i>j</i>)	2.824		1 Fe(<i>j</i>)	2.560
	1 Dy(<i>d</i>)	2.945		2 Fe(<i>k</i>)	2.563
Fe(6 <i>g</i>)	2 Fe(<i>k</i>)	2.439	Fe(18 <i>k</i>)	1 Dy(<i>d</i>)	2.953
	2 Fe(<i>k</i>)	2.447		1 Dy(<i>b</i>)	2.953
	4 Fe(<i>j</i>)	2.447		2 Fe(<i>f</i>)	2.824
	2 Fe(<i>f</i>)	2.589		1 Fe(<i>j</i>)	3.337
	2 Dy(<i>d</i>)	3.199		1 Fe(<i>g</i>)	2.439
				1 Fe(<i>g</i>)	2.447
				2 Fe(<i>k</i>)	2.449
				1 Fe(<i>j</i>)	2.549
				1 Fe(<i>j</i>)	2.554
				1 Fe(<i>j</i>)	2.563
				1 Fe(<i>j</i>)	2.569
				1 Fe(<i>f</i>)	2.636
				1 Dy(<i>b</i>)	3.120
				1 Dy(<i>d</i>)	3.126
				1 Dy(<i>b</i>)	3.281

TABLE V. Interatomic distances ($\text{\AA}$) of the nearest-neighbors in hexagonal ThFe_5 .

<i>Atom</i>	<i>Neighbors and distances</i>		<i>Atom</i>	<i>Neighbors and distances</i>	
Fe(2 <i>c</i>)	4 Fe(<i>g</i>)	2.504	Fe(3 <i>g</i>)	4 Fe(<i>c</i>)	2.504
	2 Fe(<i>g</i>)	2.506		4 Fe(<i>c</i>)	2.558
	2 Fe(<i>c</i>)	2.951		4 Th(<i>a</i>)	3.261
	1 Fe(<i>c</i>)	2.960			
	1 Th(<i>a</i>)	2.951			
	2 Th(<i>a</i>)	2.955			

TABLE VI. Interatomic distances (Å) of the nearest-neighbors in $\text{Er}_6\text{Fe}_{23}$.

<i>Atom</i>	<i>Neighbors and distances</i>		<i>Atom</i>	<i>Neighbors and distances</i>	
Fe(4b)	8 Fe(f_2)	2.537	Fe(32 f_1)	3 Fe(f_1)	2.445
	6 Er(e)	3.565		3 Fe(d)	2.462
Fe(24d)	4 Fe(f_1)	2.462		3 Fe(f_2)	2.583
	4 Fe(f_2)	2.621		3 Er(e)	3.037
	4 Er(e)	3.054	Fe(32 f_2)	1 Fe(b)	2.537
				3 Fe(f_1)	2.582
				3 Fe(d)	2.621
				3 Fe(f_2)	2.929
				3 Er(e)	2.950

TABLE VII. Interatomic distances (Å) of the nearest-neighbors in DyFe_3 .

<i>Atom</i>	<i>Neighbors and distances</i>		<i>Atom</i>	<i>Neighbors and distances</i>	
Fe(3b)	6 Fe(h)	2.532	Fe(18h)	1 Fe(c)	2.506
	6 Dy(c)	3.024		1 Fe(c)	2.532
Fe(6c)	3 Fe(h)	2.506		1 Fe(b)	2.532
	3 Fe(h)	2.532	2 Dy(c)	4 Fe(h)	2.562
	3 Fe(c)	2.958		2 Dy(c)	2.931
	3 Dy(a)	2.958		1 Dy(c)	3.067
			2 Dy(a)	3.274	

References

- [1] J. J. Croat, J. F. Herbst, R. W. Lee and F. E. Pinkerton, J. Appl. Phys. 55, 2078 (1984).
- [2] M. Sagawa, S. Fujimura, M. Togawa and Y. Matsuura, J. Appl. Phys. 55, 2083 (1984).
- [3] J. J. Croat, J. Less-Common Met. 148, 7 (1989).
- [4] L. Pareti, F. Bolzoni, M. Solzi, and K. H. J. Buschow, J. Less-Common Met. 132, L5 (1987).
- [5] X. C. Kou, X. K. Sun, Y. C. Chuang, R. Grössinger, and H. R. Kirchmayr, J. Magn. Magn. Mater. 80, 31 (1989).
- [6] S. Hirosawa, Y. Matsuura, H. Yamamoto, S. Fujimura, and M. Sagawa, H. Yamauchi, J. Appl. Phys. 59, 873 (1986).
- [7] S. Sinnema, R. J. Radwanski, J. J. M. Franse, D. B. de Mooij, and K. H. J. Buschow, J. Magn. Magn. Mater. 44, 333 (1984).
- [8] C. D. Fuerst, J. F. Herbst, and E. A. Alson, J. Magn. Magn. Mater. 54-57, 567 (1986).
- [9] R. Grössinger, R. Krewenka, X. K. Sun, R. Eibler, H. R. Kirchmayr, and K. H. J. Buschow, J. Less-Common Met. 124, 165 (1986).
- [10] J. Q. Xie, C. H. Wu, Y. C. Chuang, and F. M. Yang, J. Magn. Magn. Mater. 75, 361 (1988).
- [11] J. F. Herbst and W. B. Yelon, J. Appl. Phys. 57, 2343 (1985).
- [12] R. L. Streever, Phys. Rev. B 19, 2704 (1979).

- [13] J. H. Wernick and S. Geller, *Act. Crystallogr.* 12 662 (1959).
- [14] A. M. van Dipepen, K. H. J. Buschow and J. S. van Wieringen, *J. Appl. Phys.* 43, 645 (1972).
- [15] J. Laforest and J. S. Shah, *IEEE Trans. Magn. Mag-9*, 3 217 (1973).
- [16] J. B. A. A. Elemans and K. H. J. Buschow, *Phys. Stat. sol. (a)* 24, 393 (1974).
- [17] Y. D. Zhang, J. I. Budnick, M. Wojcik, E. Potenziani II, A. T. Pedziwiatr, and W. E. Wallace, *Phys. Rev. B* 36, 8213 (1987).
- [18] J. F. Herbst, J. J. Croat, R. W. Lee, and W. B. Yelon, *J. Appl. Phys.* 53, 250 (1982).
- [19] D. E. Tharp, Ying-chang Yang, O. A. Pringle, Gary J. Long, and W. J. James, *J. Appl. Phys.* 61 4334 (1987).
- [20] J. F. Herbst and W. B. Yelon, *J. Appl. Phys.* 60, 4224 (1986).
- [21] H. M. van Noort, D. B. De Mooij, and K. H. J. Buschow, *J. Less Common Met.* 115, 155 (1986).
- [22] P. Deppe, M. Rosenberg, S. Hirose, and M. Sagawa, *J. Appl. Phys.* 61, 4337 (1987).
- [23] F. Bolzoni, F. Leccabue, O. Moze, L. Pareti, M. Solzi, and A. Deriu, 61 61, 5369 (1987).
- [24] J. J. Bara, B. F. Bogacz, and A. Szytula, *J. Magn. Magn. Mater.* 75, 293 (1988).
- [25] H. Honma and H. Ino, *IEEE Trans. Magn. MAG-23*, 3116 (1987).
- [26] M. Matsui, M. Doi, and T. Shimizu, *IEEE Trans. Magn. MAG-23*, 3113 (1987).

- [27] Y. Sano, H. Onodera, H. Yamauchi, and H. Yamamoto, 79, 67 (1989).
- [28] R. S. Perkins and P. Fischer, *Solid State Commun.* 20 1010 (1976).
- [29] R. Kumar, W. B. Yelon, and C. D. Fuerst, *J. Appl. Phys.* 63, 3725 (1988).
- [30] P. C. M. Gubbens, *Ph.D thesis*, University of Leiden, (1977).
- [31] Y. C. Chang, J. Jiang and Y. C. Chuang, *J. Less-Common Met.* 107, 1 (1985).
- [32] J. I. Budnick, M. Wojcik, Y. D. Zhang, in *Proceedings of the NATO Advanced Study Institute on Supermagnets, Hard Magnetic Materials*, edited by G. J. Long and F. Grandjean (Kluwer Academic Publishers, Boston), 283 (1991).
- [33] D. H. Ryan, Z. Altounian, J. O. Ström-Olsen, and W. B. Muir, *Phys. Rev. B* 39, 4730 (1989).
- [34] T. C. Gibb, *Mössbauer Spectroscopy* (Chapman & Hall, London) 1976.
- [35] U. Gonser, *Mössbauer Spectroscopy* (Springer-Verlag, New York), 1975.
- [36] N. A. Eissa and G. Denardo, *Applications of Nuclear Gamma Resonance Spectroscopy* (World Scientific, Singapore), 1988.
- [37] G. J. Long and F. Grandjean, in *Proceedings of the NATO Advanced Study Institute on Supermagnets, Hard Magnetic Materials*, edited by G. J. Long and F. Grandjean (Kluwer Academic Publishers, Boston), 355 (1991).
- [38] F. Grandjean, G. J. Long, O. A. Pringle, and J. Fu, *Hyper. Interact.* 62, 131 (1990).
- [39] N. W. Ashcroft and N. D. Mermin, *Solid State Physics* (Saunders College, Philadelphia), 1976.
- [40] H. J. Lipkin, *Ann. Phys.* 9, 332 (1960).

- [41] S. Ofer, I. Nowik, and S. G. Cohen, In *Chemical Applications of Mössbauer Spectroscopy*, edited by V. I. Goldanski and R. H. Herber, (Academic Press, New York), 427 (1968).
- [42] A. Abragam, *The Principles of Nuclear Magnetism* (Oxford University Press, Clarendon, London-New York) 1961.
- [43] G. J. Bowden, J. Phys. F. Metal. Phys. **3**, 2206 (1973).
- [44] P. Raj and S. K. Kulshreshtha, J. Physique **41**, 1487 (1980).
- [45] K. H. J. Buschow, J. Appl. Phys. **42**, 3433 (1971).
- [46] Supplied carrier free by New England Nuclear Medical Products, DuPont/NEN, N. Billerica, Massachusetts.
- [47] L. X. Liao, Z. Altounian, and D. H. Ryan, J. Appl. Phys. **67**, 4821 (1990).
- [48] L. X. Liao, D. H. Ryan, and Z. Altounian, Rev. Sci. Instrum. (submitted) 1991.
- [49] *International Tables for x-ray crystallography, Vol. III* (kynoch, Birmingham, 1962), Table 3.2.2E.
- [50] F. Salvat and J. Paradellada, Nucl. Instr. Method in Physics Research, **B1**, 70 (1984).
- [51] J. G. Mullen and J. Stevenson, Nucl. Instr. and Meth. **153**, 77 (1978).
- [52] J. G. Mullen, A. Djedid, C. Holmes, G. Schupp, L. Crow, and W. Yelon, Nucl. Instr. and Meth. **B14**, 323 (1986).
- [53] S. Bocquet, R. J. Pollard and J. D. Cashion, Hyp. Int. **40**, 2503 (1990).
- [54] J. F. Herbst, J. J. Croat, and W. B. Yelon, J. Appl. Phys. **57**, 4086 (1985).

- [55] P. Villars and L. D. Calvert, *Pearson's Handbook of Crystallographic Data for Intermetallic Phases* (American Society of Metals, Metals Park, OH, 1985).
- [56] Q. Ling, J. M. Cadogan, and J. M. D. Coey, *Hyper. Interact.* **28**, 655 (1986).
- [57] R. Fruchart, P. L'Heritier, P. Dalmas de Réotier, D. Fruchart, P. Wolfers, J. M. D. Coey, L. P. Ferreira, R. Guillen, P. Vulliet, and A. Yaouanc, *J. Phys. F* **17**, 483 (1987).
- [58] H. Onodera, A. Fujita, H. Yamamoto, M. Sagawa, and S. Hirosawa, *J. Magn. Magn. Mater.* **68**, 6 (1987).
- [59] P. Panissod, M. Wojcik and E. Jedryka, in *Proceedings of the NATO Advanced Study Institute on Supermagnets, Hard Magnetic Materials*, edited by G. J. Long and F. Grandjean (Kluwer Academic Publishers, Boston), 315 (1991).
- [60] D. Givord, F. Givord, R. Lemaire, W. J. James and J. S. Shah, *J. Less. Common Met.* **29**, 389 (1972).
- [61] P. C. M. Gubbens, J. J. van Loef, and K. H. J. Buschow, *J. Phys.* **35**, Suppl. c-6, 617 (1974).
- [62] W. Steiner and R. Haferl, *Phys. Stat. sol. (a)* **42**, 739 (1977).
- [63] R. Coehoorn, *Phys. Rev. B* **39**, 13072 (1989).
- [64] P. C. Gubbens, and K. H. J. Buschow, *Phys. Status solid: A* **34**, 729 (1976).
- [65] P. C. Gubbens, A. M. van der Kraan, and K. H. J. Buschow, *Solid State Commun.* **19**, 335 (1976).
- [66] K. Schwarz and P. Mohn, *J. Phys. F* **74**, L129 (1984).
- [67] K. Hardman, W. J. James, and W. B. Yelon, *J. Phys. Chem. Solids* **41**, 1105 (1980).

- [68] S. K. Arif, D. St P. Bunbury, G. J. Bowden and R. K. Day, *J. Phys. F: Metal Phys.* **5**, 1048 (1975).
- [69] A. M. van der Kraan, J. N. J. van der Velden, J. H. F. van Apeldoorn, P. C. M. Gubbens, and K. H. J. Buschow, *Phys. Stat. Sol. (a)* **35**, 137 (1976).
- [70] S. K. Arif, D. St P. Bunbury and G. J. Bowden, *J. Phys. F: Metal Phys.* **5**, 1792 (1975).
- [71] D. E. Tharp, O. A. Pringle, W. J. James, G. K. Marasinghe, G. Long, D. Xie, and W. B. Yelon, *J. Less-Common Met.* **149**, 363 (1989).
- [72] P. C. M. Gubbens and A. M. van der Kraan, *J. Magn. Magn. Mater.* **9**, 349 (1978).
- [73] L. Gelato, *J. Appl. Cryst.* **14**, 141 (1981).
- [74] W. B. Pearson, *The Crystal Chemistry and Physics of Metals and Alloys* (Wiley-Interscience, New York/Toronto), pp. 135 (1972).